

Suitable corrosivity categories/durability ranges

C

Paint system ISO 12944-5	Low	Medium	High	Very high
C4.07	X	X	X	X
C5.03	X	X	X	

TEC4.07 Very high
TEC5.03 High

2-COMPONENT COMBI Paint systems 300 µm

1 1.8.2018

2-COMPONENT COMBI paint systems consist of different types of paint chemistries. These direct to metal two layer paint systems have excellent adhesion to steel. Epoxy paints have from their nature good mechanical and corrosion protection properties. Polyurethane paints and fast curing polyaspartics have good gloss and colour retention properties outdoors.

Where excellent gloss and colour retention is expected of the surface finish, it is recommended to add 40 µm dry film of TEKNODUR 0250, 0290 or 295-900 clear coat as a top layer on top of the polyurethane (PUR) or polyaspartic (PAS) paint systems described below. Please consult TEKNOS representative for choosing the most suitable product.

These paint systems are designed for corrosivity categories C4 – C5 with durability classes very high - high.

Paint		A1	A2	A3	A4	A5	A6
TEKNOPLAST HS 150	EP	2x150 µm					
TEKNOMASTIC COMBI 80-500	EP		2x150 µm				
INERTA 271	EP			2x150 µm			
TEKNODUR COMBI 340-811	PUR				3x100 µm		
TEKNODUR COMBI 3430 -series	PUR					3x100 µm	
TEKNODUR COMBI 3560 -series	PAS						2x150 µm
Total film thickness		300 µm	300 µm	300 µm	300 µm	300 µm	300 µm
Paint system VOC, g/m ²		129	73	79	118	172 - 225	20 - 180

Example of Teknos paint system code	Example of paint system structure
TEC4.07/VH/A1	ISO 12944-5/C4.07-EP (EP300/2-FeSa 2½).
TEC5.03/H/A4	ISO 12944-5/C5.03-PUR (PUR300/3-FeSa 2½)

These Teknos painting systems have been designed in accordance with ISO 12944:2017-2018 standards. In order to reach the durability ranges in specified corrosivity categories, care must be taken to ensure full compliance of steel construction design, steel prework and surface preparation quality with ISO 12944 standards.

Surface preparation Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods.

Steel surfaces: Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1).

For more detailed information about of the above-mentioned products please see individual product data sheets.