
TYPE	Water borne primer.
USE	Wooden laths and doors as well as MDF and fibre board indoors. Before using the product, the manufacturer should be contacted to check the suitability of the product for the object in question.
SPECIAL PROPERTIES	The paint dries quickly and it is easy to rub down. AQUAFILLER 1151-00 gives a surface that has good filling properties and that can be top coated with water borne paints. Recommended for roller coating and vacumat.

TECHNICAL DATA

Solids	64 ± 2 % by weight 42 ± 2 % by volume
Total mass of solids	Approx. 990 g/l
Volatile organic compound (VOC)	See Safety Data Sheet.
Drying time at +23 °C / 50 % RH (glass plate 120 µm)	
- surface dry	After 30 min.
- touch dry	After 40 min.
- overcoatable	After 1 hour
	The drying times are indicative as the product is intended for use on MDF.
Thinner, cleaning	Water.
Gloss	Matt.
Colour	Light shades.

DIRECTIONS FOR USE

Surface preparation	The surface must be clean and dry. The moisture content of the wood should not exceed 20 %.
Application conditions	When coating and curing the temperature of the air, paint and surface must be 15 °C and the relative air humidity below 80 %. The best result is achieved at an air temperature between +23 - +38 °C; a relative humidity between 50-70 % and good ventilation.
Application data	Stir the product well before use. Apply the paint by roller coating. Application with undiluted paint is recommended, but the paint can be diluted with water, if required. The formation of foam caused by the application process can be reduced with the addition of 0.5 % TEKNOPAINT ADDITIVE 7901-30 defoamer (over addition may cause defoamer defects in the paint film).

ADDITIONAL INFORMATION	Storage: See label. Store in a tightly closed can. The best storage temperature is +10 °C -+25 °C. MUST NOT FREEZE.
-------------------------------	--
