

ABZIEHLACK LM 1938-00

Solvent-based 1C peelable coating

ABZIEHLACK LM 1938-00 creates an elastic coating film for temporary protection of bright metallic machine parts, tools etc. during transport and storage. The product is used as a protective coating to prevent moisture exposure and mechanical stress as well as for the protection of metal surfaces, e.g. in galvanic processes or in spray booths.



TECHNICAL DATA

Solids	Approx. 19% by weight
Theoretical spreading rate	520 g/m ² ; 1.9 m ² /kg
Colours	White.
Thinner	OWEDUR 5046-98
Density	Approx. 0.95 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil.
Application method	Conventional spraying, Brush Notes: For good peelability, 2-3 coats should be applied "wet-on-wet" (> 100 µm dry film thickness).

Surfaces coated with peelable coatings may not be exposed to weathering, otherwise the peelability will be lost. The product is unsuitable for protecting coated surfaces. The organic solvents contained in the product may attack coatings, resulting in an adhesive bond.

Application	Stir or shake the product well for several minutes before use, if necessary by machine.
--------------------	---

APPLICATION					
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles
Gravity Feed Gun	38"	undiluted	2	2.8-3.5	

Application conditions	Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.
-------------------------------	---

Drying time	+23 °C / 65% RH
- dust free	after 10 minutes
- touch dry	after 60 minutes
- through dry	after 60 minutes
Cleaning	Wash the equipment immediately after use. OWEDUR 5046-98 or OWEDUR 3502-98.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
First aid	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.