

ANTISTAIN AQUA 5210-00

Primer for spray application

ANTISTAIN AQUA 5210-00 is a water-borne industrial primer for new wood designated for exterior use such as windows and doors.

ANTISTAIN AQUA 5210-00 effectively reduces yellowing from knots and softwood with a large amount of heartwood.



TECHNICAL DATA

Fields of application	Doors, Windows
Recommended substrate	Softwood
Volatile organic compound (VOC)	See safety data sheet.
Theoretical spreading rate	5-8 m ² /l
Colours	White.
Storage	Storage temperature is +5°C - +30°C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Surface preparation	The wood must be free from wood dust and contamination. The moisture content of the wood should be approx. 13% and should not exceed 15%. Pretreatment is required for wood substrates not meeting Durability Class 3, EN 350:2016. Teknos has a range of preservative products meeting the requirements of EN 599-1, please contact Teknos for further guidance.		
Application method	Airless spraying, Air-assisted airless spraying, Electrostatic spraying		
Application	Nozzle	Pressure	Air support
	Airless flat 0.28 mm	100-110 bar	
	Air assisted airless flat 0.28 mm	80-100 bar	1.0-1.5 bar
Application conditions	Stir thoroughly before use. Optimum temperature for products and surroundings: +18°C - +22°C. Optimum relative air humidity: Approx. 50%. Wet film range 125-200 µm.		
Thinning	The product is delivered ready for use.		

Drying time	+23°C / 50% RH
-dry to handle	2-3 h
-fit for sanding and overcoating	3-4 h*
	*As the film thickness is of paramount importance for the effectiveness of the product, it is important not to sand the surface too much. The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation, and film thickness.
Coating system	Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather.
Cleaning	Water.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.