

# AQUAFILLER 1190-00

## Primer

AQUAFILLER 1190-00 is a water-borne primer based on acrylic.

Use: Wooden laths and doors as well as MDF and fibre board indoors.

Before using the product, the manufacturer should be contacted to check the suitability of the product for the object in question.

AQUAFILLER 1190 dries quickly and it is easy to sand. AQUAFILLER 1190 levels out well and gives a surface that can be top coated with water-borne paints.

## TECHNICAL DATA

<b>Fields of application</b>	Interior doors
<b>Recommended substrate</b>	MDF, Softwood
<b>Binder</b>	Acrylic
<b>Solids</b>	37 ±2% by volume
<b>Total mass of solids</b>	Approx. 700 g/l
<b>Volatile organic compound (VOC)</b>	Approx. 18 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Theoretical spreading rate</b>	8 m <sup>2</sup> /l (wet film 125 µm, dry film 45 µm) 6 m <sup>2</sup> /l (wet film 167 µm, dry film 60 µm)
<b>Colours</b>	White.
<b>Gloss (60°)</b>	Matt
<b>Thinner</b>	Water.
<b>Storage</b>	The storage stability is shown on the label. Store in a tightly closed container. The best storage temperature is +10°C - +25°C.  Must not freeze.

## DIRECTION FOR USE

<b>Surface preparation</b>	The surface must be clean and dry. The moisture content of the wood is to be below 20%.
<b>Application method</b>	Spray
<b>Application</b>	Stir thoroughly before use. Application with undiluted product is recommended, but the product can be diluted with water, if required.

**Application conditions**

During the application and drying period the temperature of the ambient air, the surface and the product shall be above +15°C and the relative air humidity below 80%.

The best result is achieved when the temperature of the air is +23°C - +38°C, the relative humidity of the air 50 - 70% and the ventilation is good.

<b>Drying time</b>	+23°C / 50% RH (glass plate 120 µm)
--------------------	-------------------------------------

<b>- dust free</b>	30 min
--------------------	--------

<b>- touch dry</b>	40 min
--------------------	--------

<b>Cleaning</b>	Water.
-----------------	--------

**HEALTH AND SAFETY****Safety and precaution measures**

See safety data sheet.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.