BIORA 7



Water-borne acrylate dispersion paint intended for use on interior walls. It is easy to apply and produces a matt, even film.

BIORA 7 can be applied onto concrete, plaster, filler, brick and building board surfaces.



TEKNOS



TECHNICAL DATA

Certificates, approvals and classification	Allergy label (Finland), M1 classification, Nordic Ecolabel, Finnish Key Flag
Fields of application	Ceilings, Indoor wall
Recommended substrate	Pre-primed boards, Concrete, Building board, Filler, Gypsum board, Acrylate paint
Solids	Approx. 38% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/a): 30 g/l. The product's VOC: max. 30 g/l.
Practical spreading rate	Previously painted surface: 10 - 12 m²/l.
	Filler and wood fibre board: 7 - 10 m²/l.
	Concrete and plastered surface: 4 - 8 m²/l
Colours	Base paints 1 (white) and 3, which can be tinted to obtain the shades in Interior
	Colour Card.
Tinting system	Teknomix
Gloss (60°)	Matt
Thinner	Water.
Density	Approx. 1.3 g/ml
Storage	Must not freeze.
Packaging	Base paints 1 and 3: 0.9 l, 2.7 l, 9 l.

DIRECTION FOR USE

Surface preparationClean new surfaces from dust and dirt. Wash previously painted surfaces with
RENSA SUPER paint cleaner. Matt down hard or gloss surfaces by sanding and
thereafter remove the dust. Remove all of the old paint from the surfaces which
have been painted with glue paint or lime wash. For smoothing of irregularities
in the surface choose a suitable filler from the SILORA series. The dried filler is
sanded down and the dust removed.



- · ·	
Priming	Paint concrete, plaster, filler, brick, chipboard, gypsum board and fibre board surfaces straight on with BIORA 7 interior paint or prime with BIORA PRIMER primer and ceiling paint. Spray filler ceilings, which are not waterproof, are recommended to be primed with solvent borne primer e.g. FUTURA 3 Adhesion primer. Steel surfaces are primed with FERREX AQUA anticorrosive paint.
Application method	Brush, Roller, Spray Suitable airless nozzle size 0.017 - 0.021".
Application	Stir thoroughly before use. Apply once or twice.
Application conditions	The surface to be treated has to be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process.
Thinning	The product is thinned with water when needed.
Drying time	+23°C / 50% RH
- dust free	½ h
- overcoatable	1 h
	The drying process will be slower in cold and/or damp.
Washability and wear resistance	Wear resistance of the painted surface is moderate. Wet scrub resistance, class 1 according to EN 13300 (ISO 11998). Lasts over 5 000 brushings, SFS 3755.
Cleaning	Warm water and RENSA BRUSH brush cleaner. Wash the equipment
	immediately after use.
HEALTH AND SAFETY	
HEALTH AND SAFETY	immediately after use. See safety data sheet. CHEMICAL PROPERTIES AND SAFETY
HEALTH AND SAFETY	immediately after use.
HEALTH AND SAFETY	immediately after use. See safety data sheet. CHEMICAL PROPERTIES AND SAFETY The product is not classified as hazardous according to Regulation (EC)
HEALTH AND SAFETY	immediately after use. See safety data sheet. CHEMICAL PROPERTIES AND SAFETY The product is not classified as hazardous according to Regulation (EC) 1272/2008.
HEALTH AND SAFETY	 immediately after use. See safety data sheet. CHEMICAL PROPERTIES AND SAFETY The product is not classified as hazardous according to Regulation (EC) 1272/2008. Recommended safety precautions when using the product: Avoid unnecessary skin contact. Use work clothes to protect against paint
HEALTH AND SAFETY	 immediately after use. See safety data sheet. CHEMICAL PROPERTIES AND SAFETY The product is not classified as hazardous according to Regulation (EC) 1272/2008. Recommended safety precautions when using the product: Avoid unnecessary skin contact. Use work clothes to protect against paint splashes.



ADDITIONAL INFORMATION

Maintenance instructions

The final forming of the film takes approx. 4 weeks under normal circumstances and after that the ultimate durability and hardness is reached. Before this the surface must be treated with care.

The surface can be cleaned by light wiping. Use a damp cleaning cloth, soft sponge or similar for cleaning. Avoid coarse brushing or heavy abrasion.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.