

DRYWOOD OPTIFINISH G70

Water-borne topcoat

DRYWOOD OPTIFINISH G70 is an industrial water-borne gloss intermediate and topcoat for interior and exterior wooden joinery and other wood constructions.



DRYWOOD OPTIFINISH G70 can be used as an industrial topcoat system within BRL0817 (Conept III).

DRYWOOD OPTIFINISH G70 is a quick drying product, has a good adhesion, high durability, very low water uptake, good elasticity, and gloss retention. The product has nice filling and leveling properties, is easy to sand, and has good overcoatability properties. It also has good blocking properties, surface hardness, and scratch resistance.



TECHNICAL DATA

Certificates, approvals and classification	KOMO Certificate BRL 0817 (33135)
Fields of application	Exterior doors, Windows
Recommended substrate	Hardwood, Modified wood, Softwood, Plywood, Modified wood fibre boards, Thermally modified wood
Solids	Approx. 36% by volume depending on the colour.
Volatile organic compound (VOC)	Approx. 45 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	Approx. 8 m ² /l at 50 µm dry film thickness
Colours	Base 1, 2 and 3 (white and opaque colours). Tintable in almost any opaque colour.
Gloss (60°)	Gloss
Thinner	Water.
Density	1.02-1.2 kg/l depending on the colour.
Storage	Shelf-life is at least 24 months in unopened and closed packaging. Keep containers tightly closed after use. Must not freeze.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Surface preparation	The surface to be treated must be dry, clean, and free from dust.
----------------------------	---

Application method	Airless spraying, Air-assisted airless spraying
Application	Stir thoroughly before use.
Application conditions	Min. +15 °C.
Drying time	
- overcoatable	With drying times longer than one week, light sanding is necessary before a next layer can be applied.
- through dry	See KOMO-certificate for drying conditions or min. 48 h at min. 15 °C and max. 60% RH at 100 µm dry film thickness.
	The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation, and film thickness.
Cleaning	Water.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

ADDITIONAL INFORMATION

Waste management	Material and all related packaging must be disposed in a safe way in accordance with full requirements of local authorities.
-------------------------	--

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.