

# **DRYWOOD OPTIFINISH TR MATT**

# Water-borne intermediate and topcoat

DRYWOOD OPTIFINISH TR MATT is a water-borne matt translucent industrial intermediate and topcoat for interior and exterior wooden joinery and other wood constructions. The product can also be used as a primer.



DRYWOOD OPTIFINISH TR MATT is a quick drying product with good penetration into the wood and good wet adhesion, high transparency, and excellent colour and gloss retention. The product has high durability, low water-uptake, and excellent water resistance, long lasting elasticity, high blocking resistance, and good scratch resistance. The product has nice filling and leveling properties, is easy to sand, and has good overcoatability properties.











## **TECHNICAL DATA**

Certificates, approvals and classification	KOMO Certificate BRL 0814 (32998), KOMO Certificate BRL 0817 (33135)
Fields of application	Exterior doors, Windows
Recommended substrate	Hardwood, Softwood, Modified wood, Plywood, Modified wood fibre boards, Thermally modified wood
Solids	Approx. 33% by volume depending on the colour.
Volatile organic compound (VOC)	Approx. 15 g/l (DIRECTIVE 2010/75/EU) See safety data sheet. The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	Approx. 6 m²/l at 60 μm dry film thickness.
Colours	Base T (translucent colours). Tintable in almost all translucent colours.
Tinting system	Teknocolor
Gloss (60°)	Matt
Thinner	Water.
Density	Approx. 1.03-1.10 kg/l depending on the colour.
Storage	Storage temperature is +5°C - +30°C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use. Must not freeze.
Packaging	Available in a range of standard pack sizes.

DRYWOOD OPTIFINISH TR MATT



#### **DIRECTION FOR USE**

Surface preparation	The wood must be free from wood dust and contamination. The moisture
	content of the wood should be approx. 13% and should not exceed 15%.
	Pretreatment is required for wood substrates not meeting Durability Class 3,
	EN 350:2016. Teknos has a range of preservative products meeting the
	requirements of EN 599-1, please contact Teknos for further guidance.
Application method	Airless spraying, Air-assisted airless spraying
Application	Stir thoroughly before use.
Application conditions	Min. +8°C.
Drying time	Min. +15°C / max. 60% RH
- overcoatable	Min. 4 h .
	With drying times longer than one week, light sanding is necessary before a next
	layer can be applied.
- through dry	See KOMO-certificate for drying conditions or min. 48 h at min. +15°C and max.
	60% RH at 120 μm dry film thickness.
	The drying times are approximate and may vary according to wood quality,
	temperatures, humidity, ventilation, and film thickness.
Cleaning	Water.

#### **HEALTH AND SAFETY**

Safety and precaution measures See safety data sheet.

### **ADDITIONAL INFORMATION**

Material and all related packaging must be disposed in a safe way in accordance Waste management

with full requirements of local authorities.

#### Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.