

# DRYWOOD PRIMER UV RC

## Primer

DRYWOOD PRIMER UV RC is a 100% UV-curing industrial primer for interior and exterior use on wooden plywood and board material. The product should be used as a primer system together with DRYWOOD TG PRIMER CC.



DRYWOOD PRIMER UV RC cures with UV-light. It prevents wood fibres to raise, it has good adhesion and is easy to sand.



## TECHNICAL DATA

<b>Recommended substrate</b>	Plywood
<b>Solids</b>	Approx. 100% by volume
<b>Volatile organic compound (VOC)</b>	Approx. 25 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Theoretical spreading rate</b>	Approx. 33 m <sup>2</sup> /l at 30 µm dry film thickness.
<b>Density</b>	1.4-1.6 kg/l depending on the colour.
<b>Storage</b>	Keep containers tightly closed after use. Must not freeze. Shelf-life minimum 6 months in unopened and closed packaging.
<b>Packaging</b>	Available in a range of standard pack sizes.

## DIRECTION FOR USE

<b>Surface preparation</b>	The surface to be treated must be dry, clean, and free from dust.
<b>Application method</b>	Roller coating
<b>Application</b>	Stir thoroughly before use.
<b>Application conditions</b>	At temperatures of at least +8°C.  Intermediate sanding is recommended. Always sand before a next water-borne primer is applied.
<b>Drying time</b>	
<b>- fully cured</b>	The needed UV-dosage is depending on the film thickness.
<b>Drying methods</b>	Curing with a combination of Hg and Ga lamps.
<b>Cleaning</b>	Clean equipment after use with suited cleaners as ethanol or acetone. Do not dilute.

## HEALTH AND SAFETY

**Safety and precaution measures** See safety data sheet.

## ADDITIONAL INFORMATION

**Waste management** Material and all related packaging must be disposed in a safe way in accordance with full requirements of local authorities.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.