

DUPLEX 4553-20

Water-soluble, 1C primer and sealing coating for interior use

DUPLEX 4553-20 is a water-soluble, low-tension, abrasion-resistant 1C primer and sealing coating for the low-emission, odourless treatment of wood parquet floors and stripped wooden floor boards in a direct two or three layer process. The coating has a low tendency to stick to the side edges and can therefore be used without a primer. The product is resistant to light and yellowing.





TECHNICAL DATA

Certificates, approvals and classification	Swiss environmental label UE II, class B		
Fields of application	Floors		
Binder	Acrylate		
Solids	Approx. 27% by weight		
Volatile organic compound (VOC)	Approx. 74 g/l (DIRECTIVE 2010/75/EU)		
	The VOC value provided is the average value for factory produced products, and		
	consequently it will be subject to variations between individual products		
	covered by this Technical Data Sheet.		
Theoretical spreading rate	120 g/m²; 8.3 m²/kg		
Colours	Colourless.		
Gloss (60°)	20		
Density	Approx. 1.02 g/ml		
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.		

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating
	removal: Sand



Application method	Brush, Roller				
	When renovating or coa	ting exotic wood species or hard	lwood species, we		
	-	recommend using RENO GRUND 3300.			
	Do not use on pear wood without a primer. Risk of film formation faults. When using on dark woods please refer to the instructions in our VTM 5564				
	"White discolouration" in the areas around the joints of sealed dark wood flo				
Application		•			
	machine.	Stir or shake the product well for several minutes before use, if necessary by			
	Indennie.				
	Smoothed, sanded and dedusted	Product	Applied Quantity		
	Primer	DUPLEX 4553	120 g/m ²		
	Intermediate sanding	With grain 120-150			
	Recoating	DUPLEX 4553	1-2x 120 g/m²		
	For furthe	For further application proposals please ask our representative.			
Application conditions	Recommended temperature for surroundings and product: +15°				
	apply below +10°C. Ideal surface and object temperature for application:				
		+18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems			
		must be adjusted well in advance.			
Drying time	+23°C / 65% RH	·			
- dust free	after 2 hours				
- overcoatable	after 4 hours				
- fit for sanding		after 4 hours			
- through dry	after 7 days When using non-slip carpet underlay please ensure that only qualities that are				
	suitable for water-borne	suitable for water-borne coatings are used (contact supplier or manufacture			
Cleaning	Wash the equipment im	Wash the equipment immediately after use. VERDÜNNER 1000-98			
HEALTH AND SAFETY					
Safety and precaution measures	See safety data sheet.				

First aid

local regulations are in force.

hygiene and equipment must be observed.

We recommend wearing personal protective clothing even in cases where no

CH: The precautions according to local regulations (SUVA) with respect to



ADDITIONAL INFORMATION

Maintenance instructions

Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580.

For more information on wood floor surface treatments and their use, visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.