

# FERREX AQUA

## Anticorrosive paint

FERREX AQUA is a water-borne anticorrosive pigmented anticorrosive paint and adhesion primer. Finish: semimatt.



Anticorrosive paint and adhesion primer for iron and steel surfaces as well as aluminium outdoors and indoors. The adhesion of FERREX AQUA on zinc-coated (galvanized) surfaces as well as on prefabrication primers is also excellent.

The pigmentation of FERREX AQUA effectively prevents underfilm corrosion.

FERREX AQUA can be overcoated with nearly all Teknos water- and solvent-borne paints for sheet-iron roofs, furniture and houses.



## TECHNICAL DATA

<b>Certificates, approvals and classification</b>	M1 classification		
<b>Fields of application</b>	Roof		
<b>Recommended substrate</b>	Sheet-iron, Metal, Cast iron		
<b>Solids</b>	Approx. 42 % by volume		
<b>Volatile organic compound (VOC)</b>	EU VOC limit value (kat A/i): 140 g/l. The product's VOC: max. 140 g/l.		
<b>Theoretical spreading rate</b>	<b>Dry film (µm)</b>	<b>Wet film (µm)</b>	<b>Theoretical spreading rate (m<sup>2</sup>/l)</b>
	40	100	10
<b>Practical spreading rate</b>	8 - 10 m <sup>2</sup> /l depending on application technique, substrate and the quality of surface.		
<b>Colours</b>	Grey (T1380) and white (T1326).		
<b>Gloss (60°)</b>	Semi-matt		
<b>Thinner</b>	Water.		
<b>Density</b>	Approx. 1,3 g/ml		
<b>Storage</b>	Must not freeze.		
<b>Packaging</b>	0.5 l, 1 l, 3 l, 10 l.		

## DIRECTION FOR USE

<b>Surface preparation</b>	Surfaces to be painted are cleaned from dirt, grease, oil and other impurities. RENSA STEEL washing agent, solvent wiping etc. is used for cleaning. Rust and corrosion are removed from the surfaces using scraping, wire-brushing, sanding, blast-cleaning or other suitable method. Old, glossy surfaces are roughened using sanding, blast-cleaning or other suitable method. Loose and poorly adherent old paint or coating is removed. Aluminium surfaces are roughened using sanding, blast-cleaning or other suitable method.
<b>Application method</b>	Brush, Spray Suitable airless nozzle size 0.011 - 0.015".
<b>Application</b>	Stir thoroughly before use.
<b>Application conditions</b>	The surface to be treated has to be dry. During the application and drying period (note also the temperature of the night following the application) the temperature of the ambient air, the surface and the product shall be above +10°C and the relative air humidity below 80%. If the temperature of the surface to be painted exceeds +40°C, the application properties and the adhesion of the paint may deteriorate.
<b>Drying time</b>	+23°C / 50% RH
<b>Touch dry</b>	3 h
<b>Overcoatable</b>	16 h
<b>Overcoatable</b>	The drying process will be slower in cold and/or damp.
<b>Top coating and suitable top coats</b>	Water-borne outdoor paints, e.g. KIRJO AQUA paint for sheet-iron roofs, NORDICA EKO house paint, VISA opaque wood stain, SILOKSAN FACADE silicone emulsion paint, SILOKSAN ANTI-CARB protective paint. Solvent-borne outdoor paints, e.g. WINTOL oil paint. Furniture paints: paints from FUTURA AQUA and FUTURA series. Water-borne interior paints, e.g. paints from EKORA, TEKNOSPRO and TIMANTTI series and TEKNOFLOOR AQUA floor paint. Solvent-borne interior paints, e.g. TEKNOFLOOR floor paint.
<b>Resistance</b>	Weather resistance: Moderate. Can also be left without a top coat.
<b>Cleaning</b>	Warm water and RENSA BRUSH brush cleaner.

## HEALTH AND SAFETY

**Safety and precaution measures** See safety data sheet.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.