

FLOOR 4500-25

Water-soluble 1C floor sealing coating for interior use

FLOOR 4500 is a water-soluble, highly abrasion-resistant 1C floor sealing coating for low-emission, odourless treatment of practically all softwoods and hardwoods. FLOOR 4500 is also suitable as a top sealing coating on MINOPRIMER AQUA 6700 for anhydrite floors. The product is resistant to light and yellowing.





TECHNICAL DATA

Certificates, approvals and classification	Swiss environmental label UE II, class C, EMICODE EC 1 Plus		
Fields of application	Floors		
Solids	Approx. 32% by weight		
Volatile organic compound (VOC)	Approx. 78 g/l (DIRECTIVE 2010/75/EU)		
	The VOC value provided is the average value for factory produced products, and		
	consequently it will be subject to variations between individual products		
	covered by this Technical Data Sheet.		
Theoretical spreading rate	120 g/m²; 8.3 m²/kg		
Colours	Colourless.		
Tinting system	Largo		
Gloss (60°)	25		
Density	Approx. 1.03 g/ml		
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.		
DIRECTION FOR USE			
Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand		
Application method	Brush, Roller		
	When renovating or coating exotic wood species, we recommend using RENO		
	GRUND 3300.		
	Do not use on pear wood without a primer. Risk of film formation faults.		
	When using on dark woods please refer to the instructions in our VTM 5564 "White discolouration" in the areas around the joints of sealed dark wood floors.		



Application	Stir or shake the proc machine.	Stir or shake the product well for several minutes before use, if necessary by machine.			
		APPLICATION ADVICE			
	Intensification of parquet	Intensification of parquet			
		Product	Applied Quantity		
	Primer	RENO GRUND 3300	125 g/m²		
	or	PARKETTGRUND 4510	120 g/m²		
	Recoating	FLOOR 4500	120 g/m²		
	Intermediate sanding	With grain 120-150			
	Recoating	FLOOR 4500	120 g/m²		
	Parquet not grain-accentuat	Parquet not grain-accentuating			
		Product	Applied Quantity		
	Primer	PARKETT RENO GRUND NORDIC 3338	125 g/m²		
	or	NATURGRUND 4538	120 g/m²		
	Recoating	FLOOR 4500	120 g/m²		
	Intemrediate sanding	With grain 120-150			
	Recoating	FLOOR 4500	120 g/m²		
	Prepared, stable substrate (a	Prepared, stable substrate (anhydrite floors)			
		Product	Applied Quantity		
	Primer	MINOPRIMER AQUA 6700	150 g/m²		
	Recoating	FLOOR 4500	120 g/m²		
	Intermediate sanding	using a green pad (sia brand)			
	Recoating	FLOOR 4500	120 g/m²		
	For fu	For further application proposals please ask our representative.			
Application conditions	apply below +10°C. I +18°C-22°C. Avoid a	Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems			
	•	must be adjusted well in advance.			
Drying time	+23°C / 50% RH (dry	+23°C / 50% RH (dry film 20 μm)			
- dust free	after 2 hours	after 2 hours			
- overcoatable	after 4 hours	after 4 hours			
- fit for sanding	after 4 hours	after 4 hours			
- through dry	after 7 days	after 7 days			
	When using non-slip	When using non-slip carpet underlay please ensure that only qualities that are			
	. .	rne coatings are used (contact supplier	• •		
Cleaning		Wash the equipment immediately after use. VERDÜNNER 1000-98			
	wash the equipment	initial and a set of the bounder of			

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.



ADDITIONAL INFORMATION

Maintenance instructions

Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580.

For more information on wood floor surface treatments and their use, visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.