

FUTURA 3

Adhesion primer

A multipurpose alkyd primer that can also be used both as primer, primer surfacer, adhesion primer and intermediate coating. Finish: full-matt.



FUTURA 3 is intended for priming of surfaces indoors and outdoors, such as furniture, chipboard, fibre board and gypsum board. Also for priming of metal surfaces indoors (also light metal and galvanized surfaces) as well as glass, ceramic tiles, PVC plastic and acid-curing paints indoors. Can also be used for painting ceilings.



TECHNICAL DATA

Certificates, approvals and classification	Finnish Key Flag
Fields of application	Detached furniture, Garden furniture
Recommended substrate	Building board, Metal, Powder paint, Wood
Solids	Approx. 50% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/i): 500 g/l. The product's VOC: max. 500 g/l.
Practical spreading rate	Applied once onto a smooth surface: 8 - 10 m ² /l. When painting untreated chipboard the spreading rate must be 5 - 6 m ² /l.
Colours	White. Can be tinted with tinting pastes. The colour accuracy is not complete.
Tinting system	Teknomix
Gloss (60°)	Full-matt
Thinner	TEKNOSOLV 1621 (solvent naphtha) or in spray application TEKNOSOLV 9500
Density	Approx. 1.4 g/ml
Packaging	White: 0.45 l, 0.9 l, 2.7 l, 9 l.

DIRECTION FOR USE

Surface preparation	Clean new surfaces from dust and dirt. Wash previously painted surfaces with RENSA SUPER paint cleaner. Wire-brush the rusty metal parts. Remove loose and poorly adherent paint coats. Remove all possible latex paints. Matt down hard or gloss surfaces by sanding and thereafter remove the dust.
Application method	Brush, Paint brush, Roller, Spray Suitable airless nozzle size 0.011 - 0.013".
Application	Stir thoroughly before use.
Application conditions	The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%.

Thinning	For painting wooden surfaces dilute the paint if needed 5 - 10 % with TEKNOSOLV 1621. When applying by spray, thin the paint 5 - 15 % by volume with TEKNOSOLV 9500.
Drying time	+23°C / 50% RH
- dust free	2 h
- overcoatable	6 h
	The drying process will be slower in cold and/or damp.
Cleaning	TEKNOSOLV 1621 (solvent naphtha) or in spray application TEKNOSOLV 9500

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet. NOTE! Because of the danger of spontaneous combustion, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.