

HELO AQUA 5

Varnish for wooden surfaces

HELO AQUA 5 is a water-borne, full-matt varnish that enhances the natural look of wood. Contains UV protection. For wooden surfaces indoors and outdoors.



Use: Wooden doors, windows and furniture indoors and outdoors. Wooden plank floors, stairs, wall and ceiling panels indoors. Product meets the requirements of toy safety standard EN 71-3:2019 for limit values for migration of chemical elements.



TECHNICAL DATA

Certificates, approvals and classification	M1 classification, EN 71-3:2019, Finnish Key Flag
Fields of application	Doors, Furniture, Panels, Stairs, Windows, Plank floors
Recommended substrate	Planed wood, Veneer, Wood
Solids	Approx. 32% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/i): 140 g/l. The product's VOC: max. 140 g/l.
Practical spreading rate	7 - 10 m ² /l.
Colours	Clear. Can be tinted to translucent shades.
Tinting system	Teknomix
Gloss (60°)	Full-matt
Thinner	Water.
Storage	Must not freeze.
Packaging	0.45 l, 0.9 l, 2.7 l.

DIRECTION FOR USE

Surface preparation	The wooden surface must be dry, carefully sanded and cleaned from dust and other impurities.
Application method	Brush, Trowel, Spray Airless spray nozzle size 0.009 - 0.015".

Application	<p>Stir thoroughly both before use and between the applications, but be careful not to let air into the product.</p> <p>Apply first a thin coat of HELO AQUA 5 varnish by brush and let it dry for at least one hour. Sand the surface and remove all sanding dust carefully. Apply a second coat of varnish and let dry for about 3 hours before applying the third coat, if needed.</p> <p>Untreated wooden plank floors: Prime with 15 % diluted HELO AQUA 80 using brush or trowel. Intersand, if necessary, and finish with 2-3 coats of 10 % diluted HELO AQUA 5 using brush or trowel. Spread out the varnish in the direction of the pattern and the grain of the wood.</p> <p>Previously varnished plank floors: It is recommended to sand the surface to bare wood and follow the instructions for untreated plank floors. If the old varnish is in good condition HELO AQUA 5 can be applied after intersanding (sandpaper n:o 100- 150) to the surface according to above mentioned instructions. In this case the adhesion needs to be tested on a small area.</p>
Application conditions	<p>During the application and drying period the temperature of the ambient air, the surface and the product shall be above +10°C and the relative air humidity below 80%.</p>
Drying time	+23°C / 50% RH
- dust free	1 - 3 h
- overcoatable	1 - 3 h
- dry to use	<p>The surfaces can be taken into use 24 hours after application of the last coat. The varnish reaches its final hardness within 1 - 2 weeks. Hard abrasion is thus to be avoided during 2 weeks after the treatment.</p>
Resistance	<p>Light resistance: Good. Contains UV protection, does not yellow.</p> <p>Note! For objects outdoors we recommend tinted varnish and avoiding use on horizontal surfaces.</p>
Cleaning	<p>Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use.</p>

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.