

HELO SOLANA WAX

Matt log wax

HELO SOLANA WAX is a water-borne protective agent for wooden surfaces. Effectively protects wood from discolouration caused by UV radiation. HELO SOLANA WAX forms a natural looking, dirt and water repellent surface. Protects wood from normal yellowing.
Finish: matt.



Use: Treatment of wooden surfaces in dry spaces indoors. For log and panel walls, panel ceilings, mouldings and interior doors. HELO SOLANA WAX is suitable for untreated and previously with wood wax treated wooden surfaces.



TECHNICAL DATA

Certificates, approvals and classification	M1 classification, Finnish Key Flag
Fields of application	Ceilings, Interior doors, Indoor wall, Mouldings, Panels, Doors
Solids	Approx. 26% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/e): 130 g/l. The product's VOC: max. 130 g/l.
Practical spreading rate	10 - 14 m ² /l applied once with brush (equals to approx. 15 - 20 µm dry film).
Colours	Clear. Can be tinted to translucent shades.
Tinting system	Teknomix
Gloss (60°)	Matt
Storage	Must be stored tightly closed and kept cool. Must not freeze.
Packaging	0.9 l, 2.7 l, 9 l.

DIRECTION FOR USE

Surface preparation	Clean new surfaces from dust and dirt. Wash surfaces previously treated with wood wax with RENSA SUPER paint cleaner. If the wooden surface has previously been varnished or oiled, the suitability of the HELO SOLANA WAX must be ensured by a test application. Remove old paint or varnish layers completely.
Application method	Brush, Cloth, Sponge, Spray

Application	<p>Stir thoroughly before use. Tinted product must also be stirred during the application, if needed. Apply once or twice.</p> <p>Apply HELO SOLANA WAX by synthetic fibre brush, sponge, cloth or spray. Suitable nozzle for airless spray is 0.013 - 0.017". In order to achieve effective protection against UV radiation apply two layers. The intensity of the shade and the absorption of the product to the wooden surface must be ensured with a test application when using tinted product. Absorption properties of the surface and possible previous treatments affect the shade.</p>
Application conditions	<p>The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +10°C and the relative air humidity below 80%.</p> <p>Good ventilation during the application and drying period quickens the drying process.</p>
Thinning	Undiluted.
Drying time	+23°C / 50% RH
- dust free	½ h
- overcoatable	1 h
	The drying process will be slower in cold and/or damp.
Cleaning	Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

ADDITIONAL INFORMATION

Maintenance instructions The final forming of the film takes approx. 3 weeks under normal circumstances and after that the ultimate durability and hardness is reached. Before this the surface must be treated with care.

The surface can be cleaned by wiping with a neutral (pH 6 - 8) detergent. Detergent and dirt are removed by wiping and/or rinsing the surface with clean water. Use a cleaning cloth, soft sponge or similar for cleaning. Avoid coarse brushing or heavy abrasion. Follow the dilution and other instructions of the detergent producer when using detergents.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.