

KIRJO AQUA 20

Semi-matt sheet-iron roof and facade paint

Water-borne acrylate-based paint containing corrosion inhibitor for sheetiron surfaces. Finish: semi-matt.



For painting of new unpainted zinc coated/galvanized sheet-iron surfaces and for maintenance painting of sheet-iron surfaces painted previously with alkyd or acrylate paints. KIRJO AQUA 20 can be applied to a new sheet-iron plate as soon as the plating is completed.

KIRJO AQUA 20 can also be used for maintenance painting of industrially paint coated sheet steel on vertical and horizontal surfaces: polyurethane, PURAL, PUREX, acrylic and PVC-Plastisol coatings.















TECHNICAL DATA

Certificates, approvals and	Finnish Key Flag		
classification			
Fields of application	Outdoor wall, Roof		
Solids	Approx. 38% by volume		
Volatile organic compound (VOC)	EU VOC limit value (kat A/i): 140 g/l. The product's VOC: max. 140 g/l.		
Practical spreading rate	7 - 8 m²/l, 40 μm dry film, applied once with brush.		
Colours	Base paints 1 and 3, which can be tinted to obtain the shades in Exterior Colour		
	Card.		
	Ready-made shades: T2504 Graphite grey, T2509 Red, T2514 Brown, T2515		
	Black.		
Tinting system	Teknomix		
Tinting system Gloss (60°)	Teknomix Semi-matt		
Gloss (60°)	Semi-matt		
Gloss (60°) Thinner	Semi-matt Water.		
Gloss (60°) Thinner Density	Semi-matt Water. Approx. 1.2 g/ml		
Gloss (60°) Thinner Density Storage	Semi-matt Water. Approx. 1.2 g/ml Must not freeze.		



DIRECTION FOR USE

Surface preparation

GALVANIZED SHEET-IRON ROOFS AND OTHER UNPAINTED GALVANIZED SURFACES: A new sheet-iron roof can be painted as soon as it is completed. This is an advantage particularly in urban climate as the unpainted iron-sheets do not get dirty prior to painting. Wash galvanized surfaces before painting with RENSA STEEL washing agent for galvanized surfaces according to the instructions for use and rinse thoroughly with fresh water. NOTE! Cleaning agent must not dry onto the surface to be painted. Remove possible rust by e.g. steel brush.

ROOF SURFACES: Remove all flaky and poorly adherent old paint as well as rust by scraping, by steel brush and/or by a machine. If the whole paint coat is, or can be assumed to be poorly adherent (e.g. paint is flaking in many areas), the paint is removed by mechanical methods or with paint remover. Bitumen paints and tars are removed totally before painting with KIRJO AQUA 20. The surface is washed with RENSA ROOF roof wash (diluted 1 part detergent: 3 parts water) and rinsed with fresh water. NOTE! Cleaning agent must not dry onto the surface to be painted.

VERTICAL/WALL SURFACES: industrially coated sheet steel - polyurethane, PURAL, PUREX, acrylic and PVC-Plastisol coatings: The type of the old coating and the suitability of KIRJO AQUA 20 for its maintenance painting must be defined before painting. If there are doubts about the suitability and adhesion, these are to be ensured by test painting. The condition of the industrial coating and its adhesion to the sheet steel must be evaluated carefully. If the old coating is badly damaged, weathered/chalked, cracking or peeling from large areas, it must be completely removed before painting with KIRJO AQUA 20. Peeling of old, poorly adherent coating cannot be stopped by maintenance painting. The surface is washed with RENSA ROOF roof wash (diluted 1 part detergent: 3 parts water) and rinsed with fresh water. NOTE! Cleaning agent must not dry onto the surface to be painted.



_			
U	rı	min	σ
			5

Apply KIRJO AQUA 20 directly to clean zinc coated and galvanized surfaces as well as thoroughly cleaned old surfaces painted with alkyd or acrylate paints. Bare steel surfaces, which are cleaned from rust are primed with FERREX AQUA Anticorrosive Paint.

Roof and horizontal surfaces, coated sheet steel - polyurethane, polyester, PURAL, PUREX, acrylic and PVC-Plastisol coatings: Priming with KIRJO AQUA paint for sheet-iron roofs by the instructions in it's TDS and top coating with KIRJO AQUA 20.

Vertical and wall surfaces, coated sheet steel - polyurethane, PURAL, PUREX, acrylic and PVC-Plastisol coatings: Priming and top coating with KIRJO AQUA 20.

Application method Application

Airless spraying, Brush

Stir thoroughly before use.

NEW UNPAINTED SURFACES: Apply the paint by brush or airless spray. When applied by a brush, apply the paint twice to a dry film thickness of 2 x 40 μm. When spray painting the total film thickness of 80 μm (wet film abt. 210 μm) may be applied as a single coat. Recommended nozzle for airless spray is 0.015 - 0.019".

MAINTENANCE PAINTING: Bare, rust-free sheet-iron surfaces of the cleaned, damaged areas are touched up with KIRJO AQUA 20. Very rusty, cleaned steel surfaces are primed with FERREX AQUA Anticorrosive Paint. The surfaces are then painted with KIRJO AQUA 20 to a dry film thickness of 40 µm.

Application conditions

The surface to be treated has to be dry. During the application and drying period (note also the temperature of the night following the application) the temperature of the ambient air, the surface and the product shall be above +10°C and the relative air humidity below 80%. If the temperature of the surface to be painted exceeds +40°C, the application properties and the adhesion of the paint deteriorate.

Thinning Dilute the product 5 - 15 % by volume by water, when required.

Drying time +23°C / 50% RH
- dust free 1 h

- overcoatable 8 h

The drying process will be slower in cold and/or damp.

Warm water and RENSA BRUSH brush cleaner. Wash the equipment

immediately after use.

HEALTH AND SAFETY

Cleaning

Safety and precaution measures

See safety data sheet.



Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.