

MOTIVO COLORATO 2070-15

Water-soluble 1C top coat for interior use

MOTIVO COLORATO 2070 is a fast-drying, water-soluble 1C top coat with very good flow properties. The product is characterised by its high elasticity and good block resistance.













TECHNICAL DATA

Certificates, approvals and	EN 71-3, Swiss environmental label UE II, class B
classification	
Fields of application	Furniture
Binder	Acrylate
Solids	Approx. 35% by weight
Volatile organic compound (VOC)	Approx. 74 g/l (DIRECTIVE 2010/75/EU)
	The VOC value provided is the average value for factory produced products, and
	consequently it will be subject to variations between individual products
	covered by this Technical Data Sheet.
Theoretical spreading rate	120 g/m²; 8.3 m²/kg
Colours	Available in all RAL and NCS-S colours or at your request.
Tinting system	Largo;Teknocolor
Gloss (60°)	15
Density	Approx. 1.19 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating
	removal: Sand, strip



Application

Stir or shake the product well for several minutes before use, if necessary by machine.

		ΔΡΡΙΙΓΔΤΙ	ON ADVICE			
Wood substrate ra	2047	ALLEGAL	OII ADDICE			
WOOd Substitute 18	100	Product		Applied (Ouantity	
Presanding		pp			Quantity	
Primer	With grain 180-220 MOTIVO COLORATO 2070			120	g/m²	
Intermediate	IVIO	TIVO COLORATO 2	.070	120	B/111	
sanding	With grain 220-240					
Recoating	MOTIVO COLORATO 2070			120 g/m²		
MDF/HDF raw						
		Product		Applied Quantity		
Presanding	V	Vith grain 180-22	0			
Primer	HYDI	HYDROFILL PREMIUM 6338		2-3x 220-250 g/m²		
Intermediate sanding	With grain 220-240					
Recoating	MO	MOTIVO COLORATO 2070		120 g/m²		
Foil-coated chipbo	ard					
	Product			Applied Quantity		
Pre-treatment	Cleaning with SPEZIALBENZIN 0530-98					
and	subsequent foil sanding with grain 180-220					
Primer	HYDROFILL PREMIUM 6338			1-2x 150-	-200 g/m²	
Intermediate sanding	With grain 220-240					
Recoating	MOTIVO COLORATO 2070		80-100 g/m²			
Plastics						
		Product		Applied Quantity		
	When requeste	d / Please take no	te of technichal			
	instru	uction sheet VTM 2	2417.			
Recoating	MO ⁻	MOTIVO COLORATO 2070			80-130 g/m²	
	For further ap	plication proposal	s please ask our r	epresentative.		
		APPLIC	CATION			
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles	
Gravity Feed Gun	35-42"	5-20 %	1.8-2.0	2-3	1-2	
Suction Cup Gun	35-42"	0-5 %	1.8-2.0	2-3	2	
Airless / Airmix		0-5 %	0.28-0.33	Material 60-80	1-2	
Spray Application	35-42"			Atomising air pres		
HVLP	35-42"	0-5 %	1.8-2.0	2-3	2	

	conditions

Recommended temperature for surroundings and product: $+15^{\circ}\text{C}-25^{\circ}\text{C}$. Do not apply below $+10^{\circ}\text{C}$.

Drying time +23°C / 65% RH

- dust free after 60 minutes

- touch dry after 45 minutes

- overcoatable after 2 hours

- fit for sanding after 2 hours

- through dry after 10 hours

Cleaning Wash the equipment immediately after use. Water, ACETON 8000-98.



MOTIVO COLORATO 2070-15

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
First aid	We recommend wearing personal protective clothing even in cases where no
	local regulations are in force.
	CH: The precautions according to local regulations (SUVA) with respect to
	hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Waste management Disposal of washing water:

It is not permitted to dispose of washing water in the mains drainage system. Add 0.5% WENALAT 2051-00 KOAGULIERUNGSLÖSUNG to the washing water

and wait for the precipitate to settle.

The clear water above and the sediment can be disposed of correctly in

accordance with the regulations of the responsible authorities.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.