

# MOTIVO COLORATO 2070-30

## Water-soluble 1C top coat for interior use

MOTIVO COLORATO 2070 is a fast-drying, water-soluble 1C top coat with very good flow properties. The product is characterised by its high elasticity and good block resistance.



### TECHNICAL DATA

<b>Certificates, approvals and classification</b>	EN 71-3
<b>Fields of application</b>	Furniture
<b>Binder</b>	Acrylate
<b>Solids</b>	Approx. 34% by weight
<b>Volatile organic compound (VOC)</b>	Approx. 74 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Theoretical spreading rate</b>	120 g/m <sup>2</sup> ; 8.3 m <sup>2</sup> /kg
<b>Colours</b>	Available in all RAL and NCS-S colours or at your request.
<b>Tinting system</b>	Teknocolor
<b>Density</b>	Approx. 1.19 g/ml
<b>Storage</b>	Storage temperature is +5°C - +30°C.

### DIRECTION FOR USE

<b>Surface preparation</b>	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
----------------------------	--

## Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE					
Wood substrate rough					
	Product			Applied quantity	
Pre-sanding	With grain 180-220				
Primer	MOTIVO COLORATO 2070			120 g/m²	
Intermediate sanding	With grain 220-240				
Recoating	MOTIVO COLORATO 2070			120 g/m²	
MDF/HDF rough					
	Product			Applied quantity	
Pre-sanding	With grain 180-220				
Primer	HYDROFILL PREMIUM 6338			2-3x 220-250 g/m²	
Intermediate sanding	With grain 220-240				
Recoating	MOTIVO COLORATO 2070			120 g/m²	
Panels coated with primer foil					
	Product			Applied quantity	
Preperation	Clean beforehand with SPEZIALBENZIN 0530-98				
and	then sand the film with grain 180-220				
Primer	HYDROFILL PREMIUM 6338			1-2x 150-200 g/m²	
Intermediate sanding	With grain 220-240				
Recoating	MOTIVO COLORATO 2070			80-100 g/m²	
Plastics					
	Product			Applied quantity	
	Only on request / Refer to VTM 2417				
Base coat	MOTIVO COLORATO 2070			80-130 g/m²	
For further application advice, please contact our representative.					
APPLICATION					
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles
Gravity Feed Gun	35-42"	5-20 %	1.8-2.0	2-3	1-2
Suction Cup Gun	35-42"	0-5 %	1.8-2.0	2-3	2
Airless / Airmix	35-42"	0-5 %	0.28-0.33	Material 60-80	1-2
				Atomising air pressure 1.0-1.5	
HVLP	35-42"	0-5 %	1.8-2.0	2-3	2

## Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.

### Drying time

- dust free
- touch dry
- overcoatable
- fit for sanding
- through dry

+23°C / 65% RH  
after 60 minutes  
after 45 minutes  
after 2 hours  
after 2 hours  
after 10 hours

## Cleaning

Wash the equipment immediately after use. Water, ACETON 8000-98.

## HEALTH AND SAFETY

### Safety and precaution measures

See safety data sheet.

## ADDITIONAL INFORMATION

### Waste management

Disposal of washing water:

It is not permitted to dispose of washing water in the mains drainage system.  
Add 0.5% WENALAT 2051-00 KOAGULIERUNGSLÖSUNG to the washing water and wait for the precipitate to settle.

The clear water above and the sediment can be disposed of correctly in accordance with the regulations of the responsible authorities.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.