

MOTIVO KLARLACK 2080-05

Water-borne, grain-accentuating 1C top coat for interior use

MOTIVO KLARLACK 2080-05 is a fast-drying, water-borne, grain-accentuating 1C top coat. The product is characterised by its high elasticity and good block resistance. MOTIVO KLARLACK 2080-05 can be used as a primer and top coat.



TECHNICAL DATA

Certificates, approvals and classification	EN 71-3
Fields of application	Furniture
Binder	Acrylate
Solids	Approx. 40% by weight
Volatile organic compound (VOC)	Approx. 63 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	100-120 g/m ² ; 9.0 m ² /kg
Colours	Colourless.
Tinting system	Largo
Gloss (60°)	5
Density	Approx. 1.03 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
Application method	Technical requirement: Adhesive strength according to DIN EN ISO 2409; Gt 0

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE					
Wood substrate raw					
	Product			Applied Quantity	
Presanding	With grain 180-220				
Stain	stain if required				
Primer	MOTIVO KLARLACK 2080			110 g/m²	
Intermediate sanding	With grain 220-280				
Recoating	MOTIVO KLARLACK 2080			110 g/m²	
For further application proposals please ask our representative.					
APPLICATION					
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles
Gravity Feed Gun	30-34"	0-5 %	1.8-2.0	2-3	2
Suction Cup Gun	30-34"	0-5 %	1.8-2.0	2-3	2
Airless / Airmix Spray Application	30-34"	0-5 %	0.15-0.23	Material 60-80	2
				Atomising air pressure 1.0-1.5	
HVLP	30-34"	0-5 %	1.8-2.0	2-3 bar	2

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.

Drying time

- dust free

+23°C / 65% RH

- touch dry

after 60 minutes

- overcoatable

after 45 minutes

- fit for sanding

after 2 hours

- through dry

after 2 hours

after 10 hours

Cleaning

Wash the equipment immediately after use. Water, ACETON 8000-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

First aid

We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Waste management

Disposal of washing water:

It is not permitted to dispose of washing water in the mains drainage system. Add 0.5% WENALAT 2051-00 KOAGULIERUNGSLÖSUNG to the washing water and wait for the precipitate to settle.

The clear water above and the sediment can be disposed of correctly in accordance with the regulations of the responsible authorities.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.