

OWEDUR SOFTLACK 3334-02

Solvent-based 2C primer and top coat for interior use

OWEDUR SOFTLACK 3334 is a solvent-based 2C primer and top coat. The coating is resistant to household chemicals. When applied to porous woods, OWEDUR SOFTLACK 3334 gives the surface a strong raw wood effect.



TECHNICAL DATA

Fields of application	Furniture, Interior doors
Binder	Polyester
Solids	Approx. 10% by weight
Volatile organic compound (VOC)	Approx. 793 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	100 g/m ² ; 10 m ² /kg
Colours	Colourless.
Tinting system	Largo
Gloss (60°)	2
Hardener	Comp. B: UNIPUR 279 1910-99
Mixing ratio (A:B)	20:1 parts by weight
Pot life, +23°C	8 h
Density	Approx. 0.88 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
Application method	Airless spraying, Air-assisted airless spraying, Conventional spraying

Application	Stir or shake the product well for several minutes before use, if necessary by machine.					
	APPLICATION ADVICE					
	Wood substrate raw					
		Product			Applied Quantity	
	Presanding	With grain 180-240				
	Primer	OWEDUR SOFTLACK 3334			80-120 g/m ²	
	Intermediate sanding	With grain 320-400				
	Recoating	OWEDUR SOFTLACK 3334			80-120 g/m ²	
	For further application proposals please ask our representative.					
	APPLICATION					
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles	
Gravity Feed Gun	18-22"	5-20%	1.4-1.8	2-3	1-2	
Airless / Airmix Spray Application	18-22"	0-5%	0.15-0.23	Material 60-80 Atomising air pressure 1.0-1.5	1-2	

Application conditions Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.

Drying time	+23°C / 65% RH
- dust free	after 15 minutes
- touch dry	after 30 minutes
- overcoatable	after 2-3 hours
- fit for sanding	after 2 hours
- through dry	after 10 hours

Cleaning Wash the equipment immediately after use. OWEDUR 3502-98

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

First aid We recommend wearing personal protective clothing even in cases where no local regulations are in force.
 CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.