

# RENSA FLOOR POLISH 4580-15

Polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish



RENSA FLOOR POLISH 4580-15 is a polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish. Maintains and protects old floors, restoring their (satin) matt or matt finish. Enhances the natural grain of the floor and intensifies its colour.

## TECHNICAL DATA

<b>Solids</b>	Approx. 100% by weight
<b>Volatile organic compound (VOC)</b>	Approx. 0 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Theoretical spreading rate</b>	25 g/m <sup>2</sup> ; 40 m <sup>2</sup> /kg
<b>Colours</b>	Colourless.
<b>Gloss (60°)</b>	15
<b>Density</b>	Approx. 1.02 g/ml
<b>Storage</b>	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

## DIRECTION FOR USE

<b>Surface preparation</b>	Every substrate must be well-cleaned, dry and free from grease and oil.
<b>Application</b>	Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Water-resistant finished parquet and cork floors		
	Product	Applied Quantity
Care	RENSA FLOOR POLISH 4580	25 g/m <sup>2</sup>
UV-sealed finished parquet		
	Product	Applied Quantity
Care	RENSA FLOOR POLISH 4580	25 g/m <sup>2</sup>
For further application proposals please ask our representative.		

<b>Application conditions</b>	Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.
-------------------------------	--

<b>Drying time</b>	+23 °C / 50% RH (dry film 20 µm)
<b>- dust free</b>	after 40 minutes
<b>- touch dry</b>	after 3 hours
<b>- overcoatable</b>	after 1 day
<b>- through dry</b>	after 6 days
<b>Cleaning</b>	Wash the equipment immediately after use.

## HEALTH AND SAFETY

<b>Safety and precaution measures</b>	See safety data sheet.
<b>First aid</b>	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

## ADDITIONAL INFORMATION

<b>Maintenance instructions</b>	Initial care: Wait for at least 3 weeks before thoroughly cleaning hardwood floors. If the floor is very dirty, use RENZA PRO CLEAN 4582-00 as a pre-treatment.  Let dry for at least 12 h, ideally overnight.  Maintenance: Remove dirt and dust with a vacuum and/or by mopping. Add 1 part of RENZA FLOOR POLISH 4580-15 to 5 l of cleaning water (equivalent to 2%).  Also refer to our brochure "Perfect parquet floor care".
<b>Additional information</b>	Adhesive strength according to DIN EN ISO 2409: GT 0 Abrasion resistance (Taber Abraser) DIN 68861: <80mg

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.