

TEKNOBLADE REPAIR 9000-20

Elastomeric coating

TEKNOBLADE REPAIR 9000-20 is a two-pack, solvent-free elastomeric coating designed for dispenser gun application. Intended for use as a repair product for refurbishment of Leading Edge Protection on Wind Turbine Blades.

Substrate types: Tested and approved on Fibre reinforced polymer and previously lacquered surface.

TEKNOBLADE REPAIR 9000-20 withstands impacts and hard abrasion. It will cure down to a temperature of -8 °C. The coating will yellow and chalk over time when exposed to UV light. However, the coating will still maintain protection against rain erosion despite the discoloration. TEKNOBLADE REPAIR 9000-20 is usually applied in 2-3 mm thickness.



TECHNICAL DATA

Solids	Approx. 100% by volume		
Total mass of solids	Approx. 1080 g/l		
Volatile organic compound (VOC)	Approx. 0 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.		
Theoretical spreading rate	Dry film (mm)	Wet film (mm)	Theoretical spreading rate (m²/l)
	2-4	2-4	0.5 depending on thickness
Practical spreading rate	The values depend on the application technique, surface conditions, overspray, etc. To obtain sufficient rain erosion protection – a film thickness below 1.5 mm is not recommended.		
Colours	White.		
Gloss (60°)	Gloss		
Hardener	Comp. B: TEKNOBLADE REPAIR HARDENER 7000		
Mixing ratio (A:B)	1:1 parts by volume		
Gel time	Approx. 80 s depending on film thickness and temperature.		
Storage	The storage stability is shown on the label. Must be stored tightly closed and kept cool and dry. Storage temperature is +5°C - +35°C.		

DIRECTION FOR USE

Surface preparation

Cleanliness: Any contamination that might be detrimental to surface preparation and coating must be removed prior to application. The cleaning method used shall ensure that water-soluble salts, dust, grease, and oils are fully removed.

Surface roughness: dense and uniform surface roughness free of dust.

Recommended sandpaper grit size: 60-80.

Coarse, dense, and clean roughness is mandatory for optimum and sound adhesion.

Additional instructive information for surface preparation and application can be found in the Teknos Application Guide.

Application

Vertical surfaces:
On vertical surfaces the required thickness of coating is achieved by a single pass with the dispenser gun.

The components must be kept at a temperature between +15°C and +50°C before use to ensure an efficient fluid flow through the static mixer tube and application tip.

NOTE: The viscosity of the product depends on the temperature.

The film thickness may be controlled on a reference plate (steel) with a dry film gauge. Recommended single-pass film thickness 2-4 mm. The curing process is exotherm and creates some heat depending on the applied film thickness. The cure will be slower at lower film thickness.

The mixing ratio and degree of curing can be controlled by measuring the hardness of the coating (Shore A method). At a temperature of +23°C a hardness of minimum 80 Shore A should be reached after 1 hour.

Application conditions

The surface which is to be coated must be dry and the substrate free of any moisture content. During the application and drying period, the temperature of the ambient air and the surface shall be above -8°C and below +50°C. The relative air humidity below 80%. The temperature of the surface to be treated must be at least +3°C above the dew point of the ambient air.

The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.

Drying time	+23 °C / 50% RH and approx. 2 mm thickness
- dust free	Approx. 6 min.
- fully cured	Approx. 1 day
	Shore A:
	15 min. ~ 70
	1 hour ~ 85
	24 hours ~ 95

Overcoatable

Surface temperature	TEKNOBLADE 9000-20	
	Minimum	Maximum
+8 °C	12 min.	24 h
+23 °C	6 min.	24 h
+30 °C	3 min.	24 h

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.