TECHNICAL DATA SHEET

2023-01-16

5

# **TEKNOCLEAR AQUA 1332-03**

## Water-borne clear lacquer

TEKNOCLEAR AQUA 1332-03 is a water-borne acrylic based clear lacquer. For all types of wood. For furniture, fittings, and other carpentry. Only for interior use.

Very fast drying clear lacquer with very good stacking properties. The product has nice "glow and depth" and low VOC.

### **TECHNICAL DATA**

| TECHNICAL DATA                  |   |  |
|---------------------------------|---|--|
| Fields of application           | Furniture, Mouldings  |  |
| Recommended substrate           | Veneer, Wood  |  |
| Solids                          | Approx. 21% by volume   |  |
|                                 | Approx. 23% by weight   |  |
| Volatile organic compound (VOC) | Approx. 12 g/l (DIRECTIVE 2010/75/EU)   |  |
|                                 | The VOC value provided is the average value for factory produced products, and    |  |
|                                 | consequently it will be subject to variations between individual products         |  |
|                                 | covered by this Technical Data Sheet.   |  |
| Gloss (60°)                     | Approx. 40-45   |  |
| Thinner                         | Water.  |  |
| Density                         | Approx. 1.02 kg/l   |  |
| Storage                         | Protected against frost and not above +30°C. Store in a tightly closed container. |  |
|                                 | The storage stability is shown on the label.                                      |  |
| Packaging                       | Available in a range of standard pack sizes.                                      |  |
|                                 |   |  |
| DIRECTION FOR USE               |   |  |
| Application method              | Airless spraying, Air-assisted airless spraying, Conventional spraying            |  |
| Application                     | Stir the product homogeneous before use.  |  |
| Drying time                     | +20°C / 50% RH  |  |
| - dry to handle                 | 1 h   |  |
| - stackable                     | 3-4 h   |  |
| - fit for sanding               | 2.5 h   |  |
| - forced drying                 | +50°C / 50% RH:   |  |
|                                 | -dry to handle: 20 min. after cooling   |  |
|                                 | -stackable: 20 min. after cooling   |  |
|                                 | -fit for sanding: 20 min. after cooling   |  |
|                                 |   |  |









| Coating system | TEKNOCLEAR AQUA 1332-03 is normally applied in two layers of 60-90 g/m <sup>2</sup> each. |
|----------------|---|
| Cleaning       | Water, TEKNOCLEAN 1949-00.  |
|                |   |

#### HEALTH AND SAFETY

| Safety and precaution | measures |
|-----------------------|----------|
|-----------------------|----------|

See safety data sheet.

#### Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.