

TEKNOCOAT AQUA 2575-13

Water-borne topcoat

Water-borne topcoat for solid wood, MDF and fibreboards. Very suitable for line application. Only for interior use.

Very fast drying. Very good stacking properties. Good levelling. Good filling properties.



TECHNICAL DATA

Fields of application	Interior doors, Panels, Mouldings, Furniture
Recommended substrate	Chipboard, MDF, Softwood, Hardwood, HDF, Masonite
Solids	Approx. 29-36% by volume Approx. 32-48% by weight depending on the amount of pigments Base 1: approx. 48% by weight, approx. 36% by volume Base 2: approx. 39% by weight, approx. 32% by volume Base 3: approx. 32% by weight, approx. 29% by volume
Volatile organic compound (VOC)	Approx. 8 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Colours	Available in different colours and tintable with TEKNOCOLOR in gloss 30.
Tinting system	Teknocolor
Gloss (60°)	Approx. 25-35
Thinner	Water.
Density	Approx. 1.04-1.24 kg/l, depending on the amount of pigments. Base 1: approx. 1.24 kg/l Base 2: approx. 1.12 kg/l Base 3: approx. 1.04 kg/l
Storage	Protected against frost and not above +30°C. Keep containers tightly closed after use. The storage stability is shown on the label.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Application method	Airless spraying, Air-assisted airless spraying, Conventional spraying
---------------------------	--

Recommended amount to be applied	90-130 g/m ²
Application	Stir the product homogeneous before use.
Drying time	+20 °C / 50% RH
- dry to handle	1 h
- stackable	2 h
- forced drying	+50 °C / 50% RH - dry to handle: 20 min. after cooling - stackable: 20 min. after cooling
Coating system	TEKNOCOAT AQUA 2575-13 is used on water-borne primers.
Cleaning	Water, TEKNOCLEAN 1949-00.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.