

TEKNOCRAFT FILLER 9210-00

Solvent-borne 2C fast-drying white filler



TECHNICAL DATA

Fields of application	Furniture, Interior doors
Recommended substrate	MDF
Solids	Approx. 64% by weight
Volatile organic compound (VOC)	Approx. 501 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	180 g/m ² ; 5.5 m ² /kg
Colours	White.
Hardener	Comp. B: TEKNOCRAFT HARDENER 9940-99
Mixing ratio (A:B)	10:1 parts by weight
Pot life, +23 °C	3 h
Thinner	TEKNOCRAFT THINNER FAST 9820-98, TEKNOCRAFT THINNER MEDIUM 9830-98, TEKNOCRAFT THINNER SLOW 9840-98.
Density	Approx. 1.4 g/ml
Storage	Storage temperature is +5 °C - +30 °C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
Application method	Airless spraying, Air-assisted airless spraying, Conventional spraying
Application	Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION					
	Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles
Gravity Feed Gun	25-30"	5-15%	1.8-2.0	1.5-2.5	1-2
Airless / Airmix Spray Application	50-60"	0-5%	0.28-0.33		1-2

Application conditions	Recommended temperature for surroundings and product: +15 °C-25 °C. Do not apply below +10 °C.
-------------------------------	--

Drying time	+23 °C / 65% RH
- dust free	10 min
- touch dry	30 min
- overcoatable	2 h
- fit for sanding	2 h
Cleaning	Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
First aid	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.