

TEKNOFLOOR 2K

Concrete paint

TEKNOFLOOR 2K is a water-borne, two-pack epoxy paint, producing a gloss surface that is hard, elastic and abrasion-resistant.



TEKNOFLOOR 2K is a paint for concrete floors. Other areas of use are walls in humid conditions and industrial areas, i.e. surfaces that require a durable, dense and easy-to-clean coating. The paint can also be applied onto cement plaster, brick and hard construction board surfaces. Examples of applications are saunas, wash rooms, cellars etc.

TEKNOFLOOR 2K has a good abrasion resistance. It withstands water, petrol, oil, grease, even strong lye solutions, splashes of solvents and temporary action by weak acids. It does not impart taste or odour to foodstuff and dries quickly, and both priming and top coating can therefore be applied within the same working day.

TEKNOFLOOR 2K is suitable for use in food preparation and packaging environments (Smithers Rapra, Certificate Number GC0069). Water-vapour permeability of TEKNOFLOOR 2K concrete paint fulfils the requirement of standard EN ISO 7783-1 class I, $s_D < 5 \text{ m}$.



TECHNICAL DATA

Certificates, approvals and classification	CE marking, M1 classification, Smithers Rapra, Finnish Key Flag
Fields of application	Floors, Stairs
Recommended substrate	Concrete
Binder	Epoxy
Solids	Approx. 45% by volume
Total mass of solids	Approx. 650 g/l
Volatile organic compound (VOC)	EU VOC limit value (kat A/j): 140 g/l. The product's VOC: max. 140 g/l.
Practical spreading rate	Depending on the roughness and absorbency of the surface. Standard value for a steel-trowelled, surface-ground concrete floor: 1. application 4 - 6 m ² /l. 2. application 7 - 9 m ² /l.
Colours	Base 1, 2 and 3 (white and opaque colours). Ready-made shade: TM-114.
Tinting system	Teknomix
Gloss (60°)	Gloss
Hardener	Comp. B: TEKNOFLOOR 2K KOVETE
Mixing ratio (A:B)	1:1 parts by volume

Pot life	1½ h
Thinner	Water.
Storage	Must be stored tightly closed and kept cool. Must not freeze.
Packaging	Base paints 1, 2 and 3 and standard colours: 0.45 l, 1.35 l, 4.5 l.

DIRECTION FOR USE

Surface preparation	<p>NEW CONCRETE SURFACES: The concrete must be at least 4 weeks old and well-hardened so that all moisture from casting is bound and the surface dry. The moisture of the concrete must not exceed 97% as relative humidity or 4% by weight (by 54 / BLY 12).</p> <p>Dense laitance is to be removed from steel-trowelled concrete by surface grinding or etching. Surface grinding is good method to remove laitance. It is usually done on new industrial floors as wet grinding in connection with casting. Brittle and powdery top layers are treated so that the solid concrete containing aggregate is exposed. Thereafter all cement dust is removed by vacuum cleaner or brush.</p> <p>Use etching if sanding is not possible. Etching is to be done with RENSA ETCHING etching liquid. Rinse the floor with water after etching and allow to dry.</p> <p>OLD CONCRETE SURFACES: Uncoated, greasy floors are cleaned by emulsion wash. After the emulsion wash possible laitance is removed by diamond grinding or etching. Flaking old paint coats and laitance can be removed by diamond grinding.</p> <p>TEKNOFLOOR 2K can be applied over other types of paint, provided that the old paint has good adhesion to the substrate. If the floor will be attacked by water, e.g. in saunas and washrooms, the surface should be roughened up by grinding. After this the floor is washed and rinsed.</p> <p>Filling: TEKNOFLOOR-KOVAKITTI is used for partial or entire stopping up of the surface and filling of holes. Smooth down the stopped-up areas at the earliest after 8 hours (at +23 °C).</p>
Application method	Airless spraying, Brush, Mohair roller Suitable airless nozzle size 0.015 - 0.018".

Application

Mixing of the paint: Mix 1 part Base to 1 part Hardener by volume immediately before use and stir thoroughly. Stir the Base before mixing so that it is homogenous. If the quantity of the mixture is more than 1 liter, use a slow-rotating hand drilling machine. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties. Ready paint is to be used within 1½ h from mixing. After this the mixture is unfit for use.

Apply two coats to new concrete floors. Dilute the paint for priming by adding 5 - 10 % water. Apply the paint generously so that the porous concrete surface is sealed. The paint is diluted by water, which is added to the ready paint mixture. Solvents must not be used for diluting!

Application conditions

The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +10 °C and the relative air humidity below 70%. Additionally, the temperature of the surface to be treated and the product must be at least +3 °C above the dew point of the ambient air. When needed arrange effective ventilation or drying, so that during the application and at least for the first 12 hours of the drying process the relative air humidity will be below 70%.

Drying time

- dust free

- fit for light traffic

- fully cured

+23 °C / 50% RH

1 h

4 h

7 days

Overcoatable

surface temperature	by itself	
	min.	max.
+10 °C	12 h	7 d
+23 °C	4 h	7 d

Increase in film thickness and rise in the relative humidity of the air in the drying space usually slow down the drying process.

Cleaning

Water and synthetic washing agent. Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

CE	
0809	
Teknos Oy, Takkatie 3, P.O. Box 107, FI-00371 Helsinki, Finland.	
13	
Declaration of Performance No. 0023	
0809-CPR-1063	
EN 1504-2:2004	
Surface protection products – Coatings	
Physical resistance (5.1)	
Abrasion resistance	Requirement: Weight loss less than 3000 mg
Capillary absorption and permeability to water	Requirement: $w < 0,1 \text{ kg/m}^2 \times \sqrt{h}$
Impact resistance	Class I: $> 4 \text{ Nm}$
Adhesion strength by pull-off test	Requirement: Rigid system with trafficking: $\geq 2,0 (1,5) \text{ N/mm}^2$
Dangerous substances	See safety data sheet

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.