TEKNOFLOOR AQUA OBJEKTSIEGEL 4555-15



Water-borne 1C floor sealing coating for interior use

TEKNOFLOOR AQUA OBJEKTSIEGEL 4555-15 is a water-borne, abrasion-resistant 1C floor sealing coating for low-emission, odourless treatment of wood parquet floors and stripped floor boards. The product is resistant to light and yellowing.

TECHNICAL DATA

Certificates, approvals and classification	Swiss environmental label UE II, class C
Fields of application	Floors
Recommended substrate	Wood
Binder	Acrylate
Solids	Approx. 31% by weight
Volatile organic compound (VOC)	Approx. 79 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	120 g/m²; 8.3 m²/kg
Colours	Colourless.
Gloss (60°)	15
Density	Approx. 1.02 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
Application method	Brush, Roller When renovating or coating exotic wood species, we recommend using TEKNOFLOOR RENO PRIMER 3300-00. Do not use on pear wood without a primer. Risk of film formation faults. When using on dark woods please refer to the instructions in our VTM 5564 "White discolouration" in the areas around the joints of sealed dark wood floors.

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Intensification of parquet		
	Product	Applied Quantity
Primer	TEKNOFLOOR RENO PRIMER 3300	125 g/m²
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Intermediate sanding	With grain 120-150	
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Alternative intensification of parquet		
	Product	Applied Quantity
Primer	TEKNOFLOOR AQUA PARQUET PRIMER 4510	125 g/m²
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Intermediate sanding	With grain 120-150	
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Lightening the parquet		
	Product	Applied Quantity
Primer	TEKNOFLOOR RENO PRIMER NORDIC 3338	125 g/m²
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Intermediate sanding	With grain 120-150	
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Alternative parquet lightening		
	Product	Applied Quantity
Primer	TEKNOFLOOR AQUA NATURE PRIMER 4538	125 g/m²
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
Intermediate sanding	With grain 120-150	
Recoating	TEKNOFLOOR AQUA OBJEKTSIEGEL 4555	120 g/m²
For further application proposals please ask our representative.		

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

Drying time

+23°C / 65% RH

- dust free

2 h

- overcoatable

4 h

- fit for sanding

4 h

- through dry

7 d

When using non-slip carpet underlay please ensure that only qualities that are suitable for water-borne coatings are used (contact supplier or manufacturer).

Cleaning

Wash the equipment immediately after use. Water, VERDÜNNER 1000-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

First aid	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Maintenance instructions	Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580. For more information on wood floor surface treatments and their use, visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.