

TEKNOFLOOR GAP 1435-00

Water-borne ready to use putty for parquet floors and woodworking applications



TEKNOFLOOR GAP 1435-00 is a water-borne, ready to use putty for filling gaps in parquet and wooden floors as well as other woodworking applications before sanding and applying water-borne primer or topcoat. The product is characterised by its fast-drying properties and good sandability.



TECHNICAL DATA

Certificates, approvals and classification	M1 classification, Swiss environmental label UE II, class B
Fields of application	Floors
Solids	Approx. 75% by weight
Volatile organic compound (VOC)	Approx. 0 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Practical spreading rate	Approx. 8 m ² /l, depending on the type and extent of joints and dents.
Colours	Oak. Birch.
Density	Approx. 1.5 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
----------------------------	--

Application method

Filling knife/steel trowel:

Mix the putty in the container with a drill paddle and pour the required amount of putty on the floor. Thin with a primer lacquer, if too thick. If too thin, add some sanding dust. Spread the putty with a steel trowel using crosswise strokes. Repeat if needed.

Trowel-fill, sand:

Can subsequently be reworked with all parquet floor primers and/or all water-soluble parquet coating systems.

Does not cause discolouration on the wood.

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

Drying time

+23°C / 65% RH

- dust free

15 min

- overcoatable

15-30 min, wider gaps 1 day

- fit for sanding

15-30 min, wider gaps 1 day

Cleaning

Wash the equipment immediately after use. Water, RENZA BRUSH.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

First aid

We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.