

# TEKNOLAC PRIMER 0168-06

## Alkyd primer

TEKNOLAC PRIMER 0168-06 is an air-drying, alkyd-borne primer that contains active anticorrosive pigments.

Use: Priming steel constructions for indoor and outdoor use.

The paint dries quickly and has excellent anticorrosive properties. It is used as anticorrosive paint in painting systems with top-coat. The paint has very good application properties.



## TECHNICAL DATA

<b>Fields of application</b>	Steel constructions		
<b>Recommended substrate</b>	Steel		
<b>Binder</b>	Alkyd		
<b>Solids</b>	48 ±2 % by volume (ISO 3233)		
<b>Total mass of solids</b>	Approx. 830 g/l		
<b>Volatile organic compound (VOC)</b>	Approx. 500 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.		
<b>Theoretical spreading rate</b>	<b>Dryfilm (µm)</b>	<b>Wet film (µm)</b>	<b>Theoretical spreading rate (m²/l)</b>
	40	83	12.0
	80	166	6.0
	As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.		
<b>Practical spreading rate</b>	The values depend on the application technique, surface conditions, overspray, etc.		
<b>Colours</b>	Red-brown. Other colours by agreement.		
<b>Gloss (60°)</b>	Full-matt		
<b>Thinner</b>	TEKNOSOLV 9502, TEKNOSOLV 1639.		
<b>Storage</b>	The storage stability is shown on the label. Store in a cool place and in tightly closed containers.		

## DIRECTION FOR USE

### Surface preparation

Remove from the surfaces any contaminants that might be detrimental to surface preparation and application. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:

**STEEL SURFACES:** Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1). Roughening the surface of thin-plate improves the adhesion of the paint to the substrate.

**OLD PAINTED SURFACES SUITABLE FOR OVERCOATING:** Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.

The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.

Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.

Prefabrication primer: KORRO PVB, KORRO E Epoxy and KORRO SS Zinc Silicate Prefabrication primers can be used, when required.

### Application method

Airless spraying

### Application

Stir thoroughly before use.

Suitable airless nozzle size 0.013 - 0.018". Spray evenly to the specified film thickness. Special care should be taken when spraying edges, corners and welding joints. Small areas can also be painted with a brush, but in this case one additional coat has to be applied in order to achieve the specified film thickness.

### Application conditions

The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%.

<b>Drying time</b>	+23 °C / 50% RH (dry film 40 µm)		
<b>- dust free</b>	20 min (ISO 9117-3:2010)		
<b>- touch dry</b>	20 min (ISO 9117-5:2012)		
<b>- forced drying</b>	80 °C / 15 min		
<b>Overcoatable</b>	<b>by itself, the TEKNOLAC series, the TEKNOSYNT series or the TEKNOLAC COMBI series</b>		
	<b>surface temperature</b>	<b>min.</b>	<b>max.</b>
	+5 °C	4 h	-
	+23 °C	40 min	-
	<p>The values given for drying times and overcoatability may vary depending on film thickness and drying conditions.</p> <p>Increase in film thickness and rise in the relative humidity of the air in the drying space usually slow down the drying process.</p>		

**Cleaning** TEKNOSOLV 9502 or TEKNOSOLV 1639.

## HEALTH AND SAFETY

### Safety and precaution measures

See safety data sheet.

NOTE! Because of the danger of spontaneous combustion, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.