

TEKNOPOX PRIMER 7-00

Fast drying epoxy primer

TEKNOPOX PRIMER 7-00 is a fast curing two-pack epoxy primer containing anticorrosive pigments (zinc phosphate). The product cures also in low temperatures (above -10°C).

The paint is used as anticorrosive coating, primer or intermediate coat in painting systems suited for fast recoating with another layer or in automated painting systems. It is also suitable for anticorrosive systems for road and rail transport vehicles.

The very smooth, matt surface, hard, mechanically resistant and well attached to subjects. The surface is resistant to atmospheric conditions. Exposed to direct sun radiation, the surface may chalk or change the shade.



TECHNICAL DATA

Fields of application	Machinery, Steel constructions, Transportation equipment		
Recommended substrate	Steel		
Binder	Epoxy		
Solids	65±1% by volume (ISO 3233)		
Total mass of solids	Approx. 1200 g/l		
Volatile organic compound (VOC)	Approx. 320 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.		
Theoretical spreading rate	Dry film (µm)	Wet film (µm)	Theoretical spreading rate (m²/l)
	80	123	8.1
	100	154	6.5
	150	230	4.3
	As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.		
Practical spreading rate	The values depend on the application technique, surface conditions, overspray, etc.		
Colours	TO-880 dark grey, TO-010 white, RAL 7011		
Gloss (60°)	Matt		
Hardener	Comp. B: TEKNOPOX HARDENER 7377		
Mixing ratio (A:B)	7:1 parts by volume		

Pot life, +23 °C	3 h
Thinner	Not needed. If needed (eg. rise in viscosity) use TEKNOSOLV 9506.
Storage	The storage stability is shown on the label. Store in a cool place and in tightly closed containers.

DIRECTION FOR USE

Surface preparation	<p>Remove from the surfaces any contaminants that might be detrimental to surface preparation and application. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:</p> <p>STEEL SURFACES: Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1). Roughening the surface of thin-plate improves the adhesion of the paint to the substrate.</p> <p>OLD PAINTED SURFACES SUITABLE FOR OVERCOATING: Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating. From the bare steel surfaces the rust is removed to preparation grade at least St 2 (ISO 8501-1).</p> <p>The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment. Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.</p>
Application method	Airless spraying, Conventional spraying, Brush

Application

Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. Before application the base and hardener are mixed in right proportion. Stir thoroughly down to the bottom of the vessel. Mixing by machine is recommended, for example a slow-rotating hand-drill equipped with a mixer. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties.

Apply by airless spray, air spray or brush (only for small areas). For brush painting it is recommended to thin paint (abt. 3% of thinner) and to paint several times to achieve typical dry film thickness. Airless spray parameter:
Nozzle size 0.013 - 0.017"

Nozzle pressure 20 - 30 MPa For air spray application it is recommended to thin the paint to 20-25 seconds according to Ford cup Ø4. When preparing painting specification, depending on subject and type of construction, different dry film thickness than recommended can be assumed. During airless spray application typical dry film thickness range is between 80 and 300 µm. Different dry film thickness than recommended causes change in theoretical spreading rate, wet film thickness, weight of dry film thickness, drying time, overcoating time and ready for handling time.

Application conditions

During the application and drying period the temperature of the ambient air shall be above -10°C, of the paint should be over +15°C and the relative air humidity below 85%. The minimum temperature of the surface shall be above -5°C (frost- and ice-free surface) and at least 3°C higher than dew point of the ambient air. Adequate ventilation during application and drying period is recommended.

Cleaning	TEKNOSOLV 9506
----------	----------------

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.