

TEKNORAN COMBI 1485-09

Single coat paint based on oxirane ester

TEKNORAN COMBI 1485-09 is a two-component, isocyanate-free single coat paint with high solids content and based on oxirane ester. Contains active anti-corrosive pigments. Product coating on steel surfaces within the engineering industry. The solvent emissions of the paint are low due to the high volume solids content.

The paint dries both in elevated and in room temperatures. Welding of the painted surface is to be avoided.



TECHNICAL DATA

Fields of application	Machinery, Steel constructions, Transportation equipment								
Recommended substrate	Aluminium, Steel, Zinc								
Solids	Approx. 68% by volume								
Total mass of solids	Approx. 1300 g/l								
Volatile organic compound (VOC)	Approx. 265 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.								
Theoretical spreading rate	<table border="1"><thead><tr><th>Dry film (µm)</th><th>Wet film (µm)</th><th>Theoretical spreading rate (m²/l)</th></tr></thead><tbody><tr><td>80</td><td>117</td><td>8.5</td></tr></tbody></table>	Dry film (µm)	Wet film (µm)	Theoretical spreading rate (m ² /l)	80	117	8.5		
Dry film (µm)	Wet film (µm)	Theoretical spreading rate (m ² /l)							
80	117	8.5							
	As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.								
Practical spreading rate	The values depend on the application technique, surface conditions, overspray, etc.								
Colours	By agreement.								
Tinting system	Teknotint								
Gloss (60°)	TEKNORAN HARDENER 1475-00: gloss TEKNORAN HARDENER 1475-51: semigloss								
Hardener	Comp. B: TEKNORAN HARDENER 1475-00 or TEKNORAN HARDENER 1475-51								
Mixing ratio (A:B)	2:1 parts by volume								
Pot life, +23 °C	4 h								
Thinner	Standard thinners: TEKNOSOLV 9511, TEKNOSOLV 6622 and TEKNOSOLV 6120-00. Other thinners suitable for the product: see Application.								

Storage	The storage stability is shown on the label. Store in a cool place and in tightly closed containers.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Surface preparation	<p>Remove from the surfaces any contaminants that might be detrimental to surface preparation and application. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:</p> <p>STEEL SURFACES: Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1). Roughening the surface of thin-plate improves the adhesion of the paint to the substrate. When using chemical pretreatment the suitability of the treatment is to be checked from the paint manufacturer.</p> <p>ZINC SURFACES: Hot-dip-galvanized steel structures that are exposed to atmospheric corrosion can be painted if the surfaces are sweep blast-cleaned (SaS) till matt all over. Suitable cleaning agents are, e.g. aluminium oxide and natural sand. It is not recommended according to standard ISO 12944-5 to paint hot-dip-galvanized objects that are subjected to immersion strain. Painting of hot-dip-galvanized objects that are subjected to immersion strain must be discussed separately with Teknos. It is recommended that new zinc-coated thin-plate structures are treated with sweep blast-cleaning (SaS). Thin-plate surfaces that have been weathered to matt can be treated also with RENSA STEEL washing agent for galvanized surfaces.</p> <p>ALUMINIUM SURFACES: Treat the surfaces with RENSA STEEL washing agent for galvanized surfaces. Surfaces that are exposed to weathering are also roughened up with sweep blast-cleaning (AlSaS) or sanding.</p> <p>OLD PAINTED SURFACES SUITABLE FOR OVERCOATING: Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.</p> <p>The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.</p> <p>Additional instructive information for surface preparation can be found in</p>
----------------------------	---

standards EN ISO 12944-4 and ISO 8501-2.

KORRO PVB Prefabrication Primer and KORRO E Epoxy Prefabrication Primer can be used, when required.

Application method

Airless spraying

Application

Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. Before application the base and hardener are mixed in right proportion. Stir thoroughly down to the bottom of the vessel. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties.

Apply preferably by airless spray as only this method provides the recommended film thickness in a single operation. Suitable airless nozzle size 0.011 - 0.013". Brush can be used for touching up and painting small areas.

Slow thinner: TEKNOSOLV 1640. Used e.g. when painting large surfaces and when the temperature is above room temperature.

Fast thinner for electrostatic spraying: TEKNOSOLV 1639.

Application conditions

The surface to be treated has to be dry.

During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%.

Drying time

+23°C / 50% RH (dry film 80 µm)

- dust free

1 h (ISO 9117-3:2010)

- touch dry

4 h (DIN 53150:1995)

- forced drying

+80°C / 30 min.

Overcoatable

Surface temperature	by itself	
	min.	max.
+10°C	24 h	-
+23°C	2 h	-

Increase in film thickness and rise in the relative humidity of the air in the drying space usually slow down the drying process.

Cleaning

TEKNOSOLV 9511, TEKNOSOLV 6622, TEKNOSOLV 6120-00.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.