

TIMANTTI CLEAN

Semi-matt special acrylate

Semi-matt water-borne acrylate dispersion paint which contains BioCote® silver phosphate glass antimicrobial technology to preserve the coating surface and prevent colonisation and degradation caused by microbial growth on the paint film once applied to the intended substrate.



For indoor use in spaces where wall and ceiling surfaces must be easy to clean and resistant to abrasion. Recommended objects, where special acrylate improves the functionality of the spaces, are hospitals, health centres and other public health premises, nursing homes, kindergartens, schools and other public spaces, as well as e.g. food industry spaces.

TIMANTTI CLEAN can be applied to primed concrete, plaster, filler, brick and building board surfaces according to the instructions. TIMANTTI CLEAN is also suitable for repainting old alkyd and dispersion paint coats.





















TECHNICAL DATA

Certificates, approvals and classification	Allergy label (Finland), ISO 22196, M1 classification, Finnish Key Flag
Active ingredient	TIMANTTI CLEAN enhanced with BioCote® antimicrobial technology has been tested for antimicrobial performance in accordance with ISO 22196:2011 and exhibited a minimum of 95% and up to 99.99% reduction in the population of Escherichia Coli and Methicillin Resistant Staphylococcus Aureus (MRSA). Testing was carried out by an independent laboratory.
Fields of application	Indoor wall, Bathroom, Kitchen
Recommended substrate	Pre-primed boards, Building board, Concrete, Filler, Gypsum board, Acrylate paint
Solids	Approx. 37% by volume
Volatile organic compound (VOC)	EU VOC limit value (cat A/a): 30 g/l. The product's VOC: max. 30 g/l.
Practical spreading rate	6 - 8 m²/l.
Colours	Base paints 1 (white) and 3, which can be tinted to obtain the shades in Interior Colour Card.
Tinting system	Teknomix
Gloss (60°)	Semi-matt Semi-matt
Thinner	Water.
Density	Approx. 1.3 g/ml
Storage	Must not freeze.

TIMANTTI CLEAN



Packaging Base paints 1 and 3: 0.9 l, 2.7 l, 9 l, 18 l.

Availability varies by country.

DIRECTION FOR USE

Clean new surfaces from dust and dirt. Wash previously painted surfaces with RENSA SUPER paint cleaner. Matt down hard or gloss surfaces by sanding and thereafter remove the dust. For smoothing of irregularities in the surface choose a suitable filler from the TEKNOSPRO series. The dried filler is sanded down and the dust removed. Priming HUMID AREAS AND WET ROOMS: Prime concrete, plaster, filler, brick, and building board surfaces with TIMANTTI W moisture sealer. IN DRY AREAS prime the surfaces previously mentioned with TIMANTTI 3 Primer. Application method Brush, Roller, Spray Suitable airless nozzle size 0.017 - 0.021". Application Stir thoroughly before use. Apply once or twice. Application conditions The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning Thinning The product is thinned with water when needed. Drying time - 423°C / 50% RH - dust free - 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use.		
building board surfaces with TIMANTTI W moisture sealer. IN DRY AREAS prime the surfaces previously mentioned with TIMANTTI 3 Primer. Application method Brush, Roller, Spray Suitable airless nozzle size 0.017 - 0.021". Application Stir thoroughly before use. Apply once or twice. Application conditions The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning The product is thinned with water when needed. Drying time - 23°C / 50% RH - dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Surface preparation	RENSA SUPER paint cleaner. Matt down hard or gloss surfaces by sanding and thereafter remove the dust. For smoothing of irregularities in the surface choose a suitable filler from the TEKNOSPRO series. The dried filler is sanded
Suitable airless nozzle size 0.017 - 0.021". Application Stir thoroughly before use. Apply once or twice. Application conditions The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning The product is thinned with water when needed. Drying time +23°C / 50% RH - dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Priming	building board surfaces with TIMANTTI W moisture sealer. IN DRY AREAS prime the surfaces previously mentioned with TIMANTTI 3
Application Application conditions The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning The product is thinned with water when needed. Drying time - dust free - 1h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Application method	Brush, Roller, Spray
Application conditions The surface to be treated must be dry. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning The product is thinned with water when needed. Drying time - dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment		Suitable airless nozzle size 0.017 - 0.021".
the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the application and drying period quickens the drying process. Thinning The product is thinned with water when needed. Drying time +23°C / 50% RH - dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Application	Stir thoroughly before use. Apply once or twice.
Drying time +23°C / 50% RH - dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Application conditions	the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Good ventilation during the
- dust free 1 h - overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Thinning	The product is thinned with water when needed.
- overcoatable 3 h The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Drying time	+23°C / 50% RH
The drying process will be slower in cold and/or damp. Washability and wear resistance Wear resistance of the painted surface is very good. The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	- dust free	1 h
The painted surface can be washed repeatedly. Wet scrub resistance: class 1, according to EN 13300 (ISO 11998). Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	- overcoatable	
Cleaning Warm water and RENSA BRUSH brush cleaner. Wash the equipment	Washability and wear resistance	The painted surface can be washed repeatedly.
	Cleaning	Warm water and RENSA BRUSH brush cleaner. Wash the equipment

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.



ADDITIONAL INFORMATION

Maintenance instructions

The final forming of the film takes approx. 4 weeks under normal circumstances and after that the ultimate durability and hardness is reached. Before this the surface must be treated with care.

The surface can be cleaned by wiping with a neutral (pH 6 - 8) detergent. For very dirty surfaces can also alkalescent (pH 8 - 10) detergents be used. Detergent and dirt are removed by wiping and/or rinsing the surface with clean water. Use a cleaning cloth, soft sponge or similar for cleaning. Avoid coarse brushing or heavy abrasion. Follow the dilution and other instructions of the detergent producer when using detergents.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.