

TRANEMO RÖDFÄRG

Swedish red paint, brush application

Traditional old-fashioned Swedish red ochre paint. The paint provides a surface that breathes and will protect the wood in a natural way. Finish: full-matt.



Use: Unpainted sawed plank surfaces, unplanned timber surfaces and also surfaces previously painted with Swedish red paint, e.g. on granaries, outbuildings etc.

TRANEMO RÖDFÄRG lets the walls breathe so that the moisture can evaporate through the walls.

The paint is not suitable on planed surfaces or on surfaces that have been painted with other types of paints.

Pigment: Iron oxide pigment.

Binder: Boiled linseed oil abt. 7 % of total weight. Wheat flour abt. 6 % of total weight.



TECHNICAL DATA

Fields of application	Outdoor wall
Recommended substrate	Ochre paint
Solids	Approx. 32% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/d): 130 g/l. The product's VOC: max. 130 g/l.
Practical spreading rate	Approx. 3 m ² /l.
Colours	Red.
Gloss (60°)	Full-matt
Density	Approx. 1.2 g/ml
Storage	Store in a cool place. Must not freeze.
Packaging	10 l.

DIRECTION FOR USE

Surface preparation	<p>UNTREATED SAWED PLANK AND ROUGH LOG SURFACE: Remove from the surface all loose matter, dirt, dust and mildew. If needed, use RENSA FACADE facade cleaner.</p> <p>SURFACES PREVIOUSLY PAINTED WITH RED OCHRE PAINT: Remove with steel brush all loose paint from the surface. Wash very dirty or mildewed surfaces with RENSA FACADE facade cleaner or with RENSA ANTI-MOULD protection against mildew and rinse thoroughly.</p>
----------------------------	--

Priming

First prime with TRANEMO RÖDFÄRG that has been diluted 10 - 20 % with water.

Steel surfaces are primed with FERREX AQUA anticorrosive paint.

Application method

Brush

Application

Apply by a broad brush.

Apply the paint in layers as thin as possible until good coverage has been achieved.

New surfaces are to be painted twice, surfaces previously painted with red ochre paint are to be painted once or twice.

TRANEMO RÖDFÄRG intended for brush application is not suitable for spray application.

TRANEMO RÖDFÄRG contains iron oxide pigment that is a natural pigment. Therefore little variations of colour might occur. Combine the different paint batches into a same vessel or use the natural lines e.g. corners.

NOTE! TRANEMO RÖDFÄRG contains iron sulphate that might dissolve from the painted surface and cause rust stains into light plastered or concrete socles. It might also yellow light wood surfaces.

Application conditions

During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5 °C and the relative air humidity below 80%.

The best weather for application is cloudy but dry.

Drying time

+23 °C / 50% RH

- overcoatable

4 h

The drying process will be slower in cold and/or damp.

Cleaning

Water.

HEALTH AND SAFETY**Safety and precaution measures**

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.