

UVILUX 1493-13

UV-Spray Sealer

UV-curing sealer or sealing of wooden furniture parts

The sealer has excellent adhesion on freshly sanded pine knots and may be sanded immediately upon curing.



TECHNICAL DATA

Fields of application	Furniture, Mouldings
Recommended substrate	Softwood, Hardwood
Solids	Approx. 100% by weight
Viscosity	23-30 s DIN cup 4 at +20°C.
Volatile organic compound (VOC)	Approx. 0 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Thinner	Not to be diluted.
Density	Approx. 1.1-1.4 kg/l
Storage	Should not be exposed to temperatures above +40°C. Should not be exposed to direct sunlight. Must not freeze. Store in a tightly closed container. The storage stability is shown on the label.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Application method	UV-spraying, Vacumat
Recommended amount to be applied	35-45 g/m ² .
Application conditions	The lacquer is applied by UV-spray equipment. If necessary preheated to +30°C - +35°C. The substrates may be stacked immediately upon curing.
Drying time	25-30 m/min. per lamp Ga and HG. Guideline depends on the type of lamps. For further information, please contact Teknos consultant.
Drying methods	Cures under UV-lamps.
Cleaning	TEKNOSOLV 1129-11

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.