

UVILUX 6790-02

UV Spray Lacquer

UV-curing lacquer for industrial surface treatment of wood and furniture parts.

The cured film is extremely resistant to chemicals and physical wear.

FURNITURE TEST - Field of application:

Chairs/beds/shelves: Extra high demands

Tables: High demands

Less exposed surfaces: Extra high demands



TECHNICAL DATA

Fields of application	Furniture, Mouldings
Recommended substrate	Hardwood, Softwood
Solids	Approx. 100% by weight
Total mass of solids	1100-1200 g/l \pm 2% depending on colour.
Viscosity	25-30 s DIN 4, +20°C.
Volatile organic compound (VOC)	Approx. 16 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Gloss (60°)	20 - depending on the amount applied and curing conditions.
Thinner	The product is delivered ready for use.
Density	1.10-1.20 kg/l depending on colour.
Storage	Should not be exposed to temperatures above +40°C. Should not be exposed to direct sunlight. Must not freeze. The storage stability is shown on the label. Keep containers tightly closed after use.

DIRECTION FOR USE

Application method	UV-spraying
Recommended amount to be applied	15-30 g/m ²
Drying time	
- stackable	Stacking is possible immediately after curing.
- fully cured	25-30 m/min. per lamp Ga/Hg (80 w/cm).
Drying methods	Cures under UV-lamps.

Cleaning

TEKNOSOLV 1129-11

HEALTH AND SAFETY**Safety and precaution measures**

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.