

UVILUX PUTTY 1465-00

UV-curing putty

For repair of defects in hardwood flooring and mouldings.

UVILUX PUTTY 1465-00 is developed as a one-component putty with good surface and deep cure properties. The product also has very good filling and sanding properties.



TECHNICAL DATA

Fields of application	Mouldings, Floors
Recommended substrate	Hardwood
Solids	Approx. 99% by weight
Total mass of solids	Approx. 1300 g/l
Volatile organic compound (VOC)	Approx. 9 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Colours	Clear.
Thinner	The product is delivered ready for use.
Density	1.30 kg/l
Storage	Should not be exposed to temperatures above +40°C. Should not be exposed to direct sunlight. Store in a tightly closed container. Storage stability is 1 year in unopened package. Must not freeze.

DIRECTION FOR USE

Application method	Extruder Manual and automatic application.
---------------------------	---

Drying methods

Cures under UV-lamps.

Depending on use the product can be cured under either Mercury light, Gallium light, or both.

UVILUX PUTTY 1465-00 TS 20780 CLEAR							
Semi curing				Full curing			
Hg		Ga		Hg		Ga	
Energy UVB mJ/cm ²	Peak mW/cm ²	Energy UVV mJ/cm ²	Peak mW/cm ²	Energy UVB mJ/cm ²	Peak mW/cm ²	Energy UVV mJ/cm ²	Peak mW/cm ²
				200	600	300	900
UVILUX PUTTY 1465-00 TS 20635 CLEAR							
Semi curing				Full curing			
Hg		Ga		Hg		Ga	
Energy UVB mJ/cm ²	Peak mW/cm ²	Energy UVV mJ/cm ²	Peak mW/cm ²	Energy UVB mJ/cm ²	Peak mW/cm ²	Energy UVV mJ/cm ²	Peak mW/cm ²
						600	1000

Cleaning

TEKNOSOLV 1129-11

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.