

VISA TRADITION

Alkyd oil paint

Thixotropic alkyd oil paint for outdoor use.



Use: Painting of surfaces outdoors, such as wooden facades, windows, doors, dressing boards and joinery. Developed for painting of new and press-impregnated wooden surfaces previously painted with oil or alkyd oil paints or previously treated with oil-based translucent or opaque top coat.

VISA TRADITION penetrates well into the wooden surface. VISA TRADITION has a high solids content and a good filling quality, and it produces an elastic, weather-resistant film. The application can be done at temperatures down to +5 °C.



TECHNICAL DATA

Fields of application	Outdoor wall
Binder	Alkyd
Solids	Approx. 63% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/d): 300 g/l. The product's VOC: max. 300 g/l.
Practical spreading rate	5 - 10 m ² /l depending on the substrate.
Colours	Base paints 1 (white) and 3, which can be tinted to obtain the shades in Exterior Colour Card. Ready-made shades: VIT, SVART and HUSRÖD.
Tinting system	Teknomix
Gloss (60°)	Gloss
Thinner	TEKNOSOLV 1621 (solvent naphtha).
Density	1.14 - 1.27 g/ml depending on colour.
Packaging	Base paints 1 and 3: 0.9 l, 2.7 l, 9 l. Ready-made shades: 1 l, 3 l, 10 l. Availability varies by country.

DIRECTION FOR USE

Surface preparation	<p>NEW WOODEN SURFACES:</p> <p>Treat the surface as soon as possible. At least the priming would be best done in the summer of construction.</p> <p>Remove from the surface all loose matter, dirt, dust and mildew. If needed, use RENZA FACADE facade cleaner.</p> <p>PREVIOUSLY PAINTED OR OLD WOODEN SURFACES:</p> <p>Change deteriorated wooden parts with new ones. Remove loose matter, dirt and dust. Remove the deteriorated paint coats entirely. Note, that the adhesion of an old thick paint layer to the substrate may have been weakened, therefore the paint should be removed although the paint film looks intact. The old paint layer is removed primarily by scraping or wire brushing and possibly by heating the surface with infra-red heater designed for that purpose. Secondly paint remover or blasting can be used. Wash surfaces with RENZA FACADE facade cleaner and rinse thoroughly.</p>
Priming	<p>Coat untreated wooden surface with clear priming oil from the WOODEX series. Allow to dry for one day. Prime wooden surfaces with VISA TRADITION (dilution max. 10%) or PUUPOHJA Alkyd primer.</p>
Application method	<p>Brush, Spray</p>
Application	<p>Reserve a sufficient amount of paint in the same vessel for each uniform surface. Colour differences will thus be avoided.</p> <p>Stir thoroughly before use. Apply once or twice.</p>
Application conditions	<p>The surface to be treated must be dry. The moisture content of the wood is to be below 20%. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Avoid application in direct sunlight.</p>
Drying time	<p>+23°C / 50% RH</p>
- touch dry	<p>12 h</p>
- overcoatable	<p>24 h</p> <p>The drying process will be slower in cold and/or damp.</p>
Resistance	<p>Weather resistance: Good.</p> <p>Notice that it is typical for oil paints that their colour and gloss change in the course of time.</p>
Cleaning	<p>TEKNOSOLV 1621 (solvent naphtha).</p> <p>Wash the equipment immediately after use.</p>

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

NOTE! Because of the danger of spontaneous combustion, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.