WOODEX CLASSIC

Wood stain

Slightly thixotropic, alkyd-based transparent wood stain for outdoor use. Easy to apply and penetrates into the wood and forms no uniform film after the first application. Protects the wood against weather strain by slowing the effects from moisture, UV radiation of the sun and soiling.

Use: New and previously with transparent wood stain treated wooden surfaces, e.g. log surfaces, walls, doors, window frames and fences.

Not suitable on film-forming wood stains, nor in greenhouses, hotbeds or shelters for livestock. Not suitable for indoor use.

Finnish Key Flag

TECHNICAL DATA

Application method

Certificates, approvals and

classification	
Fields of application	Exterior doors, Fences, Outdoor wall
Recommended substrate	Planed wood, Fine-sawn wood, Log, Wood, Wood stain
Solids	Approx. 20% by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/f): 700 g/l. The product's VOC: max. 700 g/l.
Practical spreading rate	Sawn timber: 5 - 8 m²/l.
	Planed timber and log: 8 - 12 m²/l.
Colours	Clear, to be tinted to translucent shades. If the parts are exposed to the
	influence of the weather never use colourless as the final treatment.
Tinting system	Teknomix
Gloss (60°)	Not defined. The product penetrates into the pores of the timber.
Density	Approx. 0.8 g/ml
Packaging	Clear: 0.9 l, 2.7 l, 9 l, 18 l.
	Availability varies by country.
DIRECTION FOR USE	
Surface preparation	Remove all loose matter, dirt and dust with wire-brush, scrubbing brush or
	scraper. Wash dirty and/or mildewed surfaces with RENSA FACADE facade
	cleaner. Rinse the surfaces thoroughly with water and allow to dry.
Priming	Coat untreated wooden surface with clear wood preservative from the
	WOODEX series. Allow to dry for one day.

Brush, Paint brush, Spray



î 🐼 🔣







Application	Stir thoroughly before use. Tinted product must also be stirred during the application, if needed.
	Apply the wood stain evenly and continuously on the whole length of the beam or timber to avoid making restart points. Treat end grain with special care.
Application conditions	The surface to be treated must be dry. The moisture content of the wood is to be below 20%. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%.
Drying time	+23°C / 50% RH
- touch dry	8 h
- overcoatable	16 h
	The drying process will be slower in cold and/or damp.
Resistance	Weather resistance: Good.
Cleaning	TEKNOSOLV 1621 (solvent naphtha).
HEALTH AND SAFETY	
Safety and precaution measures	See safety data sheet.

NOTE! Because of the danger of spontaneous combustion, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.