

WOODFLOOR 6800-30

Solvent-based 2C PU floor sealing coating for interior use

WOODFLOOR 6800-30 is a solvent-based, ready-to-roll, highly abrasion-resistant 2C PU floor sealing coating for the treatment of wood parquet floors and stripped floor boards. The product has a higher mechanical and chemical resistance than water-borne sealing coatings. Abrasion and scratch resistance meet the requirements of floors exposed to normal wear in residential areas; depending on the degree of wear, use in commercial properties is also possible without any problems.



TECHNICAL DATA

Fields of application	Floors
Binder	Acrylate
Solids	Approx. 36% by weight
Volatile organic compound (VOC)	Approx. 633 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	150 g/m ² ; 6.6 m ² /kg
Colours	Colourless.
Gloss (60°)	30
Hardener	Mix in hardener mechanically for several minutes. Comp. B: UNIPUR 279 1910-99
Mixing ratio (A:B)	5:1 parts by volume
Pot life, +23°C	16 h
Density	Approx. 1 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
---------------------	---

Application method

Brush, Roller

Polyurethane coatings may tend to stick to the sides, especially on upright slats, non-shear bonded strip and mosaic parquet floors, on underfloor heating etc. For these reasons the use of a primer is recommended.

We recommend direct application in 2-3 coats for objects subject to special stresses and substrates with a low absorbency. Dilute the first coat with 10% VERDÜNNER 5500-98.

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Parquet		
	Product	Applied Quantity
Primer	WOODFLOOR 6800	150 g/m ²
Intermediate sanding	With grain 120-150	
Recoating	WOODFLOOR 6800	150 g/m ²
	(For triple application, repeat the above procedure)	
For further application proposals please ask our representative.		

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

Drying time

+23°C / 65% RH

- dust free

after 1-2 hours

- overcoatable

after 8 hours

- fit for sanding

after 8 hours

- through dry

after 7 days

Cleaning

Wash the equipment immediately after use. VERDÜNNER 1000-98, VERDÜNNER 1300-98, VERDÜNNER 5500-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet. Do not smoke during the application and keep away from ignition sources.

First aid

We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Maintenance instructions

Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.