

**PRODUCT TYPE** Alkali resistant, ready for use colourless protective agent containing silicone, for porous rock material surfaces. Repels water and prevents penetration of moisture into the structure, but allows water vapour to evaporate from the concrete.

**USAGE** Roof tiles, stone pavings, concrete socles and other porous mineral surfaces. Not recommended for dense substrates, such as natural stone and marble.

**TECHNICAL DATA**

<b>Solids</b>	About 7,5 % by volume
<b>Volatile organic compound (VOC)</b>	EU VOC limit value (kat A/h): 30 g/l. The product's VOC: max. 30 g/l.
<b>Practical spreading rate</b>	3 - 5 m <sup>2</sup> /l
<b>Density</b>	abt. 1.0 g/ml
<b>Drying time</b>	½ h - 2 h. Overcoatable earliest the following day.
<b>Clean up</b>	Water
<b>Packages (availability varies by country)</b>	5 L, 10 L, 20 L

**SAFETY MARKINGS** See Safety Data Sheet.

---

**DIRECTION FOR USE****Surface preparation**

Clean the surface that is to be treated. Wash stone surface with RENSA ROOF roof wash.

**Application**

Apply undiluted with low pressure or airless spray 2–3 times „wet on wet“. Protect from splashes surfaces, which are not meant to be treated with TEKNOSTONE.

**Application conditions**

The surface must be clean and dry.

The temperature shall be above +5°C and the relative air humidity below 80%.

**Storage**

Must not freeze.

---

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).

---



EN\_2239\_Tuoteseloste.pdf