
PRODUCT TYPE	A semi-matt, water-borne acrylate dispersion paint for indoor use. The product has been classified to Group M1 in Emission Classification of building materials.
USAGE	The paint is suitable for use on new and previously painted concrete, plaster, filler, brick and building board surfaces. It is suitable for use on wall and ceiling surfaces that are to be resistant to washing and wear. Not to be used on doors, windows or furniture.

TECHNICAL DATA

Solids	About 39 % by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/a): 30 g/l. The product's VOC: max. 30 g/l.
Practical spreading rate	Previously painted surface 7 - 10 m ² /l Filler and wood fibre board 5 - 8 m ² /l Concrete and plastered surface 4 - 7 m ² /l

Density abt. 1.3 g/ml

Drying time at +23°C / 50% RH

- dust free after ½ h
- overcoatable after 1 h
The drying will be slowed down if the air is cool and/or humid.

Thinner, clean up Water. Wash the equipment immediately after use with water.

Finish Semi-matt

Colours Base paint 1
The paint is included in the Teknomix tinting system.

Washability and wear resistance Wear resistance of the painted surface is good.
Wet scrub resistance, class 2 according to EN 13300 (ISO 11998).
Lasts over 5 000 brushings, SFS 3755.

Packages **Base paint 1:** 18 L
(availability varies by country)

SAFETY MARKINGS See Safety Data Sheet.

DIRECTION FOR USE**Surface preparation**

Clean new surfaces from dust and dirt.
Wash previously painted surfaces with RENSA SUPER paint cleaner.
Matt down hard or gloss surfaces by sanding and thereafter remove the dust.
For smoothing of irregularities in the surface choose a suitable filler from the SILORA series. The dried filler is sanded down and the dust removed.

Priming

Steel surfaces are primed with FERREX AQUA Anticorrosive paint.
Paint galvanized surfaces with TREND 12 interior paint.
Prime other surfaces with TREND 3 primer.

Application

Before use stir the paint thoroughly.
The paint is thinned with water when needed.
Apply once or twice by brush, roller or spray.

Application conditions

The surface to be painted has to be dry. During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.
Good ventilation during the application and drying period quickens the drying process.

Maintenance instructions

The final forming of the paint film takes abt. 4 weeks under normal circumstances and after that the ultimate durability and hardness is reached. Before this the painted surface must be treated with care.

The painted surface can be cleaned by light wiping. Use a damp cleaning cloth, soft sponge or similar for cleaning. Avoid coarse brushing or heavy abrasion.

Storage

Must not freeze.

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



EN_1841_Tuoteseloste.pdf