
PAINT TYPE	Water-borne, acrylate-based adhesion primer for wash and wear resistant top coats. Finish: full-matt. The product has been classified in Emission Classification of building materials to Group M1 .
USAGE	Used as primer for dry spaces indoors, e.g. on walls and ceilings in apartments, offices, storerooms and factories. It can also be used as a top coat on ceilings and air conditioning pipes in dry spaces indoors. TEKNOSPRO POHJA can be applied to concrete, plaster, filler, brick, wood or building boards.
<hr/>	
TECHNICAL DATA	
Solids	About 34 % by volume
Volatile organic compound (VOC)	EU VOC limit value (kat A/g): 30 g/l. The product's VOC: max. 30 g/l.
Practical spreading rate	Previously painted surface 7 - 10 m ² /l Filler and wood fibre board 5 - 8 m ² /l Concrete and plastered surface 4 - 7 m ² /l
Density	abt. 1.4 g/ml
Drying time at +23°C / 50% RH	
- dust free	after ½ hour
- overcoatable	after 1 hour
	The drying will be slowed down if the air is cool and/or humid.
Thinner, clean up	Water. Wash the equipment immediately after use with water.
Finish	Full-matt
Colours	White. Can be tinted with tinting pastes to light shades according to the Interior Colour Cards. The colour accuracy is not complete.
Washability and wear resistance	Wet scrub resistance, class 2 according to EN 13300 (ISO 11998).
Packages (availability varies by country)	White: 2,7 L, 9 L, 18 L
<hr/>	
SAFETY MARKINGS	See Safety Data Sheet.

DIRECTION FOR USE**Surface preparation**

Clean new surfaces from dust and dirt.

Wash previously painted surfaces with RENSA SUPER paint cleaner.

Matt down hard or gloss surfaces by sanding and thereafter remove the dust.

Remove all of the old paint from the surfaces which have been painted with glue paint or lime wash.

Spray filler ceilings, which are not waterproof, are recommended to be primed with solvent borne primer e.g. FUTURA 3 Adhesion primer.

For smoothing of irregularities in the surface choose a suitable stopper from the TEKNOSPRO series. The dried stopper is sanded down and the dust removed.

Priming

Steel surfaces are primed with FERREX AQUA Anticorrosive paint.

Application

Before use stir the paint thoroughly.

The paint is thinned with water when needed.

Apply once or twice by brush, roller or spray.

Suitable nozzle for airless spray is 0.017 - 0.021".

Application conditions

The surface to be painted has to be dry. During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.

Good ventilation during the application and drying period quickens the drying process.

Storage

Must not freeze.

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



FI_1533_Tuoteseloste.pdf