
TYPE	Water borne primer.
USE	Wooden laths and doors as well as MDF and fibre board indoors. Before using the product, the manufacturer should be contacted to check the suitability of the product for the object in question.
SPECIAL PROPERTIES	The paint dries quickly and it is easy to sand. AQUAFILLER 1100 gives a surface that has good filling properties and that can be top coated with water borne paints.

TECHNICAL DATA

Solids by volume	40 ± 2 %
Total mass of solids	Approx. 810 g/l
Volatile organic compound (VOC)	See Safety Data Sheet.
Theoretical spreading rate	8 m ² /l (wet film 125 µm, dry film 50 µm) 6 m ² /l (wet film 167 µm, dry film 67 µm)
Drying time, +23 °C, 50 % RH (glas plate 120 µm)	
- dust free	After 30 min.
- touch dry	After 40 min.
- overcoatable	After 1 hour.
	The drying times given are indicative because the product is intended for use on wooden substrates.
Thinner	Water.
Cleaning	Water.
Gloss	Matt.
Colour	White.

DIRECTION FOR USE

Surface preparation	The surface must be clean and dry. The moisture content of the wood is to be below 20 %.
Application conditions	The temperature of the air, the surface and the paint shall be above +15 °C and the relative humidity of the air below 80 % during the time of application and drying. The best result is achieved when the temperature of the air is +23 - +38 °C; the relative humidity of the air 50-70 % and the ventilation is good.
Application	Before use stir the paint thoroughly. Apply the paint by spray. Application with undiluted paint is recommended, but the paint can be diluted with water, if required.

ADDITIONAL INFORMATION

The storage stability is shown on the label. Store in a tightly closed can. The best storage temperature is +10 °C - +25 °. **MUST NOT FREEZE.**