
PAINT TYPE	One component acid curing lacquer.
USE	Industrial surface treatment of furniture and other wooden substrates.
SPECIAL PROPERTIES	Quick drying lacquer. The lacquer provides a pleasant and smooth surface.

TECHNICAL DATA

Gloss	25, 40 and 90
Delivery viscosity	50-55 s DIN 4 at 20 °C
Specific gravity	Approx. 0.94 kg/l
Solids, weight	Approx. 27 %
Total mass of solids	Approx. 324 g/l
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	Storage: See label. Store in a tightly closed container.
Application method	Spraying, curtain coating.
Drying method	Air, oven drying

Furniture test

Field of application		Basic demands	High demands	Extra high demands
I	Chairs/beds/shelves			X
II	Tables		X	
III	Less exposed surfaces			X

DIRECTIONS FOR USE**Application data**

mixing ratio:	10 parts lacquer
Spraying:	2.5 part TEKNOSOLV 1181
Curtain coating:	1 part TEKNOSOLV 1181

Drying

At RH 55 %

	<u>20 °C</u>	<u>40 °C</u>	<u>60 °C</u>
For sanding:	2 hours	1 hour	0.5 hour
For stacking:	3 hours	1.5 hour	1 hour

The drying times are based on an applied amount of 100 g wet lacquer per m². After forced drying the substrates should be cooled to a temperature below 30 °C before stacking.

Recommended amount to be applied2 x 100 g/m²**Cleaning**

TEKNOSOLV 1181

HEALTH AND SAFETY

See Safety Data Sheet.

ADDITIONAL INFORMATION

Stir well before use.
Should not be applied or left to dry at temperatures below 18 °C.
Should not be applied or left to dry at a relative humidity above 70 %.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.
