
PAINT TYPE	UV-curing sealer.
USE	Surface sealing of pine. UVILUX SEALER 1455 provides excellent adhesion to knots.
SPECIAL PROPERTIES	The applied lacquer cures under UV-lamps. May be sanded immediately upon curing.

TECHNICAL DATA

Delivery viscosity	>100 s DIN 8 cup, 20°C
Density	approx. 1.22 kg/l
Solids, weight %	100 %
Total mass of solids	approx. 1212 g/l
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	Should not be exposed to temperatures above +40 °C. To be protected against direct sunlight. To be protected against frost. Storage: See label. Store in a tightly closed container.
Application method	Roller coating.
Drying method	Curing under UV-lamps.

DIRECTIONS FOR USE

Application data	The Sealer is ready for use.
Drying	Curing properties: 5 m/min. per lamp Hg (80 W/cm)
Recommended amount to be applied	15 g/m ² with roller.
Cleaning	If necessary, the roller may be cleaned with TEKNOSOLV 1129.

HEALTH AND SAFETY See Safety Data Sheet.

ADDEITIONAL INFORMATION The lacquer contains reactive acrylate.
The lacquer is irritating to skin and eyes.
Thus, the use of gloves and eye protection is recommended.
Take off immediately all contaminated clothing.
Application by spray is not recommended as spray mist increases the health hazards.