

<b>TYPE</b>	UV-curing lacquer.
<b>USE</b>	Surface treatment of wood and furniture parts in vacuum system or spray plant.
<b>SPECIAL PROPERTIES</b>	The cured film is extremely resistant to chemicals and physical wear.

**TECHNICAL DATA**

<b>Gloss</b>	25 depending on the amount applied and curing conditions
<b>Delivery viscosity</b>	18-21 s DIN cup 4, 20 °C
<b>Density</b>	1.22 kg/l ± 2 %
<b>Solids by weight %</b>	100%
<b>Recommended amount to be applied</b>	20-30 g/m <sup>2</sup>
<b>Volatile organic compound (VOC)</b>	See Safety Data Sheet.
<b>Storage</b>	Should not be exposed to temperatures above 40 °C. To be protected against direct sunlight. To be protected against frost. The storage stability is shown on the label. Store in a tightly closed container.
<b>Application</b>	Vacuum system or spray plant.
<b>Drying method</b>	Cures under UV-lamps.

**Furniture test**

Field of application		Basic demands	High demands	Extra high demands
I	Chairs/beds/shelves			X
II	Tables		X	
III	Less exposed surfaces			X

---

**DIRECTIONS FOR USE**

<b>Application data</b>	The lacquer is ready for use.
<b>Drying</b>	25-30 m/min. per lamp Hg (100 w/cm). The substrates may be stacked immediately after curing.
<b>Cleaning of equipment</b>	If necessary, the equipment may be cleaned with TEKNOSOLV1 129.

**HEALTH AND SAFETY** See Safety Data Sheet.

**ADDITIONAL INFORMATION** The lacquer contains reactive acrylate.  
The lacquer is irritating to skin and eyes.  
Thus, the use of gloves and eye protection is recommended.  
Take off immediately all contaminated clothing.  
Application by spray is not recommended as spray mist increases the health hazards.

---

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com).

---