
TYPE	Two component acid curing primer.
USE	As primer on chipboard and MDF prior to lacquering with enamel.
SPECIELLE EGENSKABER	Medium thixotropic primer with good levelling, filling power and sandability. Complies with the E1 requirement with regard to formaldehyde release.

TECHNICAL DATA

Delivery viscosity	35-45 s DIN 6, 20 °C.
Specific density	Approx. 1.28 kg/l
Solids, weight	Approx. 66 %
Total mass of solids	Approx. 840 g/l
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	Storage: See label. Store in a tightly closed container.
Application method	Spraying, curtain coating.

DIRECTIONS FOR USE

Application data	Mixing ratio:	10 parts Primer Approx. 1.5 part TEKNOCOAT Hardener 1399
	For spraying:	Approx. 2.5 part TEKNOSOLV 1181 or 1182 to visc. 25 s DIN 4, 20 °C
	For curtain coating:	Approx. 0.5 part TEKNOSOLV 1181 or 1182 to visc. 35 s DIN 4, 20 °C

Potlife: 24 hours when thinned to 25 s DIN 4, 20 °C.

Drying	At 55 % RH:	<u>20 °C</u>	<u>40 °C</u>	<u>60 °C</u>
	For sanding:	3 hours	45 min.	10 min.
	For stacking:	16 hours	60 min.	15 min.

Provided 150 g wet primer per m².
After forced drying cooling to 30 °C is required prior to stacking.

Recommended amount to be applied	Max. 2 x 150 g wet primer per m ² .
---	--

Cleaning	TEKNOSOLV 1181.
-----------------	-----------------

HEALTH AND SAFETY	See Safety Data Sheet.
--------------------------	------------------------

ADDITIONAL INFORMATION	The primer should be stirred well prior and after addition of hardener. Should not be applied or left to dry at temperatures below 18 °C. Should not be applied or left to dry at a relative humidity above 70 %.
-------------------------------	---