

---

<b>TYPE</b>	One-component acid curing clear lacquer.
<b>USE</b>	For all types of wood and fibreboards. Only for interior use.
<b>SPECIAL PROPERTIES</b>	Very low formaldehyde cleavage. Fast drying and good sanding properties.

---

**TECHNICAL DATA**

<b>Gloss (60°)</b>	5-80 units Gardner.
<b>Delivery viscosity</b>	40-45 s, DIN-cup 4.
<b>Density</b>	0.94-0.98 kg/l
<b>Solids, weight</b>	Approx. 33 % Approx. 25 % by volume
<b>Volatile organic compound (VOC)</b>	See Safety Data Sheet.
<b>Storage</b>	Storage: See label.
<b>System</b>	Can be used both as primer and as topcoat. Recommended amount applied 2 x 80-100 g/m <sup>2</sup> .

**DIRECTIONS FOR USE**

<b>Application method</b>	Conventional-, high pressure-, automatic spraying. Curtain coating. Dipping.		
<b>Drying</b>		<u>20 °C</u>	<u>50 °C</u>
	Dry for handling	1-2 hours	30 min.
	Dry for stacking	12 hours	1-2 hours
<b>Thinner</b>	TEKNOSOLV 1135-93.		
<b>Cleaning</b>	TEKNOSOLV 1135-93.		
<b>HEALTH AND SAFETY</b>	See Safety Data Sheet.		

---

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Material Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com).

---