
TYPE	One component clear lacquer.
USE	For all types of wood and fibreboards. Well fitted for line-application. Only for interior use.
SPECIAL PROPERTIES	Fast drying. Very good surface resistance. Good filling properties. No aromatics. Free from formaldehyde.

TECHNICAL DATA

Gloss (60°)	5-80 units Gardner
Delivery viscosity	50-55 s, DIN-cup 4, 20 °C
Specific density	0.92-0.96 kg/l
Solids, weight	Approx. 26 % Approx. 19 % by volume
Volatile organic compound (VOC)	See Safety Data Sheet.
Storage	Storage: See label.
System	Can be used both as primer and as topcoat. Recommended amount applied 2 x 80-150 g/m ² .

DIRECTIONS FOR USE

Application method	Conventional-, high-pressure- and automatic spraying. Curtain coating.		
Drying		<u>20 °C</u>	<u>50 °C</u>
	Dry for handling	60 min.	30 min.
	Dry for stacking	2 hours	1 hour
Thinner	TEKNOSOLV 1135-93.		
Cleaning	TEKNOSOLV 1135-93.		

HEALTH AND SAFETY	See Safety Data Sheet.
--------------------------	------------------------