

**TEKNOL 1881**  
**Alkyd Primer**

---

<b>PAINT TYPE</b>	Water-borne alkyd primer.
<b>USAGE</b>	Industrial priming of wooden facade boards and prefabricated units for wooden houses. To make sure that the product is suitable for the usage in question the paint manufacturer is to be contacted before the product is taken into use.
<b>SPECIAL PROPERTIES</b>	Protects the wood until it is top coated at the building site or the factory. The top coating should, however, be done as soon as possible, the next summer at the latest. Can be top coated with both dispersion and oil paints.  TEKNOL 1881-15 is a faster drying version of TEKNOL 1881.

---

**TECHNICAL DATA**

<b>Solids</b>	42 ±2% by volume
<b>Total mass of solids</b>	white abt. 715 g/l, clear abt. 600 g/l
<b>Volatile organic compound (VOC)</b>	abt. 21 g/l
<b>Theoretical spreading rate</b>	8 m <sup>2</sup> /l with diluted (dilution 1 : 1) paint (wet film 125 µm, dry film 30 µm)
<b>Drying time +23°C, the relative air humidity 50%</b> <b>dilution 1 : 1</b> <b>(glass plate 120 µm)</b> <b>- touch dry</b> <b>- overcoatable</b>	after 1 h after 2 - 3 days
<b>Thinner, clean up</b>	Water
<b>Finish</b>	Matt
<b>Colours</b>	The paint is included in the Teknomix tinting system.

**SAFETY MARKINGS** See Safety Data Sheet.

**PTO**

NOTE! Because of the danger of self-ignition, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

---

**DIRECTION FOR USE****Surface preparation**

The surface must be clean and dry.  
The moisture content of the wood is to be below 20%.

**Application conditions**

During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.

**Application**

Before use stir the paint thoroughly.  
Apply by coating machine, spray or brush. Can be diluted with water to a maximum ratio of 1 : 1 depending on the coating method and the surface.

**STORAGE**

Must not freeze. The best storage temperature is between +10 - +25°C.

---

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).

---



FI\_1078\_Tuoteseloste.pdf